

Dow Corning SILASTIC® LC-70-2004 PART A&B KIT

Category : Polymer , Thermoset , Rubber or Thermoset Elastomer (TSE) , Silicone , Silicone Rubber

Material Notes:

70 Durometer, 2 parts, 1 to 1 mix, translucent, FDA 21 CFR 177.2600 and BfR, XV, molding and injection molding grade Liquid Silicone Rubber. Fast curing speed, long pot life (72 hours), high transparency, high tear strength, low compression set. Information provided by Dow Corning

Order this product through the following link:

http://www.lookpolymers.com/polymer_Dow-Corning-SILASTIC-LC-70-2004-PART-AB-KIT.php

Physical Properties	Metric	English	Comments
Specific Gravity	1.146 g/cc	1.146 g/cc	
	@Temperature 25.0 °C	@Temperature 77.0 °F	

Mechanical Properties	Metric	English	Comments
Hardness, Shore A	67.3	67.3	
Tensile Strength, Ultimate	10.72 MPa	1555 psi	
Elongation at Break	429 %	429 %	
Tear Strength	36.8 kN/m	210 pli	

Processing Properties	Metric	English	Comments
Shelf Life	6.00 Month	6.00 Month	

Descriptive Properties	Value	Comments
Appearance	translucent	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.comEmail : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China