

Dow Corning SILASTIC® LSR 9151-200P PARTS A&B

Category : Polymer , Thermoset , Rubber or Thermoset Elastomer (TSE) , Silicone , Silicone Rubber

Material Notes:

A solventless, 2-part liquid silicone rubber available in white which has excellent water and chemical resistance, low and high temperature stability from -60 to 200 C (-76 to 392 F) and rapid cure at elevated temperatures. Information provided by Dow Corning

Order this product through the following link:

http://www.lookpolymers.com/polymer_Dow-Corning-SILASTIC-LSR-9151-200P-PARTS-AB.php

Physical Properties	Metric	English	Comments
Viscosity	13000 cP	13000 cP	dynamic

Mechanical Properties	Metric	English	Comments
Hardness, Shore A	39	39	
Tensile Strength, Ultimate	1.38 MPa	200 psi	
Elongation at Break	180 %	180 %	

Thermal Properties	Metric	English	Comments
Maximum Service Temperature, Air	200 °C	392 °F	
Minimum Service Temperature, Air	-60.0 °C	-76.0 °F	

Processing Properties	Metric	English	Comments
Pot Life	1440 min	1440 min	
Shelf Life	18.0 Month	18.0 Month	

Descriptive Properties	Value	Comments
Color	white	
Mix Ratio (X:1)	10	Base to Catalyst
Water Resistant	yes	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China