

Dow Corning SILASTIC® LSR 9390-40 PARTS A&B

Category : Polymer , Thermoset , Rubber or Thermoset Elastomer (TSE) , Silicone , Silicone Rubber

Material Notes:

40 Durometer, 2-part, 1 to 1 mix, off-white, molding grade, Liquid Silicone Rubber Information provided by Dow Corning

Order this product through the following link:

http://www.lookpolymers.com/polymer_Dow-Corning-SILASTIC-LSR-9390-40-PARTS-AB.php

Physical Properties	Metric	English	Comments
Specific Gravity	1.30 g/cc	1.30 g/cc	
	@Temperature 25.0 °C	@Temperature 77.0 °F	
Solids Content	100 %	100 %	

Mechanical Properties	Metric	English	Comments
Hardness, Shore A	40	40	
Tensile Strength, Ultimate	5.2001 MPa	754.21 psi	
Elongation at Break	510 %	510 %	
Tear Strength	1.93 kN/m	11.0 pli	
Compression Set	15 %	15 %	

Processing Properties	Metric	English	Comments
Pot Life	4320 min	4320 min	
Shelf Life	15.0 Month	15.0 Month	

Descriptive Properties	Value	Comments
Color	off-white	
Mix Ratio (X:1)	100	Base to Catalyst ETN

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.comEmail : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China