

Dow Corning SLYGARD® 537 ONE PART DIELECTRIC GEL

Category : Polymer , Adhesive , Thermoset , Silicone

Material Notes:

Information provided by Dow Corning

Order this product through the following link:

http://www.lookpolymers.com/polymer_Dow-Corning-SLYGARD-537-ONE-PART-DIELECTRIC-GEL.php

Physical Properties	Metric	English	Comments
Specific Gravity	0.980 g/cc	0.980 g/cc	
	@Temperature 25.0 °C	@Temperature 77.0 °F	
Viscosity	390 cP	390 cP	dynamic

Thermal Properties	Metric	English	Comments
Maximum Service Temperature, Air	150 °C	302 °F	
Minimum Service Temperature, Air	-45.0 °C	-49.0 °F	

Electrical Properties	Metric	English	Comments
Volume Resistivity	1.90e+15 ohm-cm	1.90e+15 ohm-cm	
Dielectric Strength	22.0 kV/mm	559 kV/in	

Processing Properties	Metric	English	Comments
Cure Time	60.0 min	1.00 hour	
	@Temperature 150 °C	@Temperature 302 °F	
Shelf Life	4.00 Month	4.00 Month	

Descriptive Properties	Value	Comments
Appearance	clear	
Flowable	yes	
Gel Hardness (Grams/Penetration)	200	
Self Leveling	yes	
Water Resistant	yes	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China