

Dow Corning XIAMETER® PMCPOHX-4012 Polymer 6000CS

Category : Polymer , Thermoset , Silicone

Material Notes:

Is chemically equivalent to DOW CORNING® 3-0113 POLYMER. OH end-blocked polydimethylsiloxane, viscosity 6,000 cP, OH/Silanol content 1,300ppm. Information provided by Dow Corning

Order this product through the following link:

http://www.lookpolymers.com/polymer_Dow-Corning-XIAMETER-PMCPOHX-4012-Polymer-6000CS.php

Physical Properties	Metric	English	Comments
Specific Gravity	0.970 g/cc	0.970 g/cc	
	@Temperature 25.0 °C	@Temperature 77.0 °F	
Viscosity	6000 cP	6000 cP	Dynamic

Processing Properties	Metric	English	Comments
Shelf Life	60.0 Month	60.0 Month	

Descriptive Properties	Value	Comments
Silanol Content (%)	0.13	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China