

## Dow Corning XIAMETER® PMCPPMX-0344 Cyclosiloxane Blend

Category : Fluid , Polymer , Thermoplastic , Siloxane

**Material Notes:**

Is chemically equivalent to DOW CORNING® 344 FLUID. A volatile methylsiloxane fluid, clear, odorless, VOC-exempt, low toxicity, low surface tension, evaporates completely at room temperature. Information provided by Dow Corning

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_Dow-Corning-XIAMETER-PMCPPMX-0344-Cyclosiloxane-Blend.php](http://www.lookpolymers.com/polymer_Dow-Corning-XIAMETER-PMCPPMX-0344-Cyclosiloxane-Blend.php)

Physical Properties	Metric	English	Comments
Specific Gravity	0.950 g/cc @Temperature 25.0 °C	0.950 g/cc @Temperature 77.0 °F	
Viscosity Measure	2.5 cSt	2.5 cSt	Kinetic/Kinematic
Surface Tension	19 dynes/cm	19 dynes/cm	

Thermal Properties	Metric	English	Comments
Melting Point	15.0 °C	59.0 °F	
Boiling Point	177 °C	351 °F	
Flash Point	52.0 °C	126 °F	Closed Cup

Processing Properties	Metric	English	Comments
Shelf Life	30.0 Month	30.0 Month	

## Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215, Fengxian District, Shanghai City, China