

Dow Corning Z-1212 CHLOROSILANE

Category : Other Engineering Material , Additive/Filler for Polymer

Material Notes:

Ethyltrichlorosilane fluid Information provided by Dow Corning

Order this product through the following link:

http://www.lookpolymers.com/polymer_Dow-Corning-Z-1212-CHLOROSILANE.php

Physical Properties	Metric	English	Comments
Specific Gravity	1.24 g/cc	1.24 g/cc	
Volatile Organic Compounds (VOC) Content	1000 g/l	1000 g/l	
Viscosity	0.606 cP	0.606 cP	dynamic
Molecular Weight	149.5 g/mol	149.5 g/mol	
Vapor Pressure	0.0560 bar @Temperature 25.0 °C	42.0 torr @Temperature 77.0 °F	

Thermal Properties	Metric	English	Comments
Melting Point	-105 °C	-157 °F	
Boiling Point	99.0 °C	210 °F	
Flash Point	14.0 °C	57.2 °F	closed cup

Processing Properties	Metric	English	Comments
Shelf Life	60.0 Month	60.0 Month	

Descriptive Properties	Value	Comments
Appearance	clear	
Hydrophobic	yes	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215, Fengxian District, Shanghai City, China