

Dow DMDA-8907 NT 7 High Density Polyethylene Resin

Category : Polymer , Thermoplastic , Polyethylene (PE) , HDPE

Material Notes:

DOW DMDA-8904 NT 7 is produced using UNIPOL™ process technology. It is intended for use in injection molding applications such as pails, industrial parts and other shipping containers. Information provided by Dow

Order this product through the following link:

http://www.lookpolymers.com/polymer_Dow-DMDA-8907-NT-7-High-Density-Polyethylene-Resin.php

Physical Properties	Metric	English	Comments
Density	0.952 g/cc	0.0344 lb/in ³	ASTM D792
ESCR 100% Igepal®	12 hour @Temperature 50.0 °C	12 hour @Temperature 122 °F	F ₅₀ ; Molded and tested in accordance with ASTM D4976; ASTM D1693
Melt Index of Compound	6.75 g/10 min @Load 2.16 kg, Temperature 190 °C	6.75 g/10 min @Load 4.76 lb, Temperature 374 °F	ASTM D1238

Mechanical Properties	Metric	English	Comments
Hardness, Shore D	59	59	Molded and tested in accordance with ASTM D4976; ASTM D2240
Tensile Strength at Break	22.8 MPa	3300 psi	Molded and tested in accordance with ASTM D4976; ASTM D638
Tensile Strength, Yield	26.9 MPa	3900 psi	Molded and tested in accordance with ASTM D4976; ASTM D638
Elongation at Break	1100 %	1100 %	Molded and tested in accordance with ASTM D4976; ASTM D638
Elongation at Yield	7.0 %	7.0 %	Molded and tested in accordance with ASTM D4976; ASTM D638
Flexural Modulus	1.07 GPa	155 ksi	2% Secant; Molded and tested in accordance with ASTM D4976; ASTM D790 B
Tensile Impact Strength	84.0 kJ/m ²	40.0 ft-lb/in ²	Molded and tested in accordance with ASTM D4976; ASTM D1822, Type S

Thermal Properties	Metric	English	Comments
Melting Point	131 °C	268 °F	Dow Method (DSC)
Crystallization Temperature	118 °C	244 °F	Dow Method (DSC)
Deflection Temperature at 0.46 MPa (66 psi)	72.8 °C	163 °F	Molded and tested in accordance with ASTM D4976; ASTM D648
Vicat Softening Point	128 °C	262 °F	ASTM D1525

Thermal Properties	Metric	English	Comments
Brittleness Temperature	≤ -76.4 °C	≤ -108 °F	Molded and tested in accordance with ASTM D4976; ASTM D746

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China