

Dow Engage® 8411 Polyolefin Elastomer

Category : Polymer , Thermoplastic , Elastomer, TPE , Thermoplastic Elastomer, Melt-Processible Rubber

Material Notes:

Description: Engage® 8411 polyolefin elastomer is an ethyleneoctene copolymer that offers excellent performance in durable injection molded industrial and consumer goods and compression molded gaskets. Engage® 8411 provides high clarity in products requiring visual inspection and allows the use of hot runner molds to enhance production efficiency. In addition, its low density can help control resin and production costs, while reducing the weight of end products. Engage® 8411 also provides good impact properties in blends with polypropylene (PP) and polyethylene (PE), especially in applications like automotive thermoplastic olefins (TPOs), requiring high melt flow modifiers. Information provided by manufacturer. This former DuPont Dow Elastomers product line is now produced by Dow Chemical.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Dow-Engage-8411-Polyolefin-Elastomer.php

Physical Properties	Metric	English	Comments
Density	0.880 g/cc	0.0318 lb/in ³	ASTM D792
Melt Index of Compound	18 g/10 min @Load 2.16 kg, Temperature 190 °C	18 g/10 min @Load 4.76 lb, Temperature 374 °F	ASTM D1238

Mechanical Properties	Metric	English	Comments
Hardness, Shore A	81	81	ASTM D2240
Hardness, Shore D	22	22	ASTM D2240
Tensile Strength, Ultimate	6.50 MPa	943 psi	508 mm/min; ASTM D638
Tensile Strength, Yield	3.00 MPa	435 psi	508 mm/min; ASTM D638
Elongation at Break	900 %	900 %	508 mm/min; ASTM D638
2% Secant Modulus	0.0219 GPa	3.18 ksi	ASTM D790

Thermal Properties	Metric	English	Comments
Melting Point	72.0 °C	162 °F	DSC, 10°C/min; DuPont Test
Vicat Softening Point	46.0 °C	115 °F	ASTM D1525

Descriptive Properties	Value	Comments
Comonomer Content	33 wt%	Dow Method (¹³C NMR/FTIR)

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China