

Dow Questra® EA514 High Heat Syndiotactic Polystyrene, 40% Glass Filled (discontinued **)

Category : Polymer , Thermoplastic , Polystyrene (PS) , Syndiotactic Polystyrene (SPS) , Syndiotactic Polystyrene (SPS) with Glass or Carbon Fiber

Material Notes:

QUESTRA® Crystalline Polymers are semi-crystalline engineering thermoplastic resins produced from styrene monomer using a proprietary metallocene catalyst system. These syndiotactic polymers are very different from conventional styrenics in structure, and properties, exhibiting excellent heat resistance with a melting temperature of 270.C, excellent moisture and chemical resistance together with a unique combination of exceptional electrical properties, toughness and processability. QUESTRA crystalline polymers are typically used as moldings, films, and fibers in Electronic, Electrical, Automotive, Consumer and Industrial, Filtration, Optical/photographic film and Specialty fiber/non-woven markets.QUESTRA EA514 is a 40% glass filled, ignition resistant polymer suitable for Electrical and Electronic applications.Data provided by Dow Chemical.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Dow-Questra-EA514-High-Heat-Syndiotactic-Polystyrene-40-Glass-Filled-nbspdiscontinued-.php

Physical Properties	Metric	English	Comments
Density	1.47 g/cc	0.0531 lb/in ³	ASTM Data
Water Absorption	0.010 %	0.010 %	

Mechanical Properties	Metric	English	Comments
Tensile Strength, Ultimate	122 MPa	17700 psi	ASTM Data
Tensile Strength, Yield	122 MPa	17700 psi	ASTM Data
Tensile Modulus	10.3 GPa	1490 ksi	ASTM Data
Izod Impact, Notched	0.910 J/cm	1.70 ft-lb/in	ASTM Data

Thermal Properties	Metric	English	Comments
CTE, linear, Parallel to Flow	25.2 µm/m-°C	14.0 µin/in-°F	ASTM data
	@Temperature 20.0 °C	@Temperature 68.0 °F	
Deflection Temperature at 0.46 MPa (66 psi)	263 °C	505 °F	Unannealed; ASTM Data
Deflection Temperature at 1.8 MPa (264 psi)	240 °C	464 °F	Unannealed; ASTM Data
Vicat Softening Point	263 °C	505 °F	
Flammability, UL94	V-0	V-0	
	@Thickness 1.60 mm	@Thickness 0.0630 in	

Electrical Properties	Metric	English	Comments
Dielectric Strength	23.6 kV/mm	599 kV/in	
Dissipation Factor	0.0010	0.0010	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China