

Dow Tyrin® CM0730 Formulation

Category : Polymer , Thermoplastic , Elastomer, TPE

Material Notes:

FormulationTyrin® CPE Elastomer

Order this product through the following link:

http://www.lookpolymers.com/polymer_Dow-Tyrin-CM0730-Formulation.php

Physical Properties	Metric	English	Comments
Mooney Viscosity	>= 37 @Temperature 121 °C	>= 37 @Temperature 250 °F	ML 1 + 4; ASTM D1646

Mechanical Properties	Metric	English	Comments
Hardness, Shore A	75	75	ASTM D2240
Tensile Strength, Ultimate	17.9 MPa	2600 psi	ASTM D412
Elongation at Break	300 %	300 %	ASTM D412
200% Modulus	0.00970 GPa	1.41 ksi	ASTM D412

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.comEmail : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China