

## DuPont Bynel® 2022 Acid-Modified Ethylene Terpolymer Adhesive Resin

Category : Polymer , Thermoplastic , EMAAA Terpolymer

### Material Notes:

Bynel® Series 2000 resins are acid-modified ethylene terpolymers with medium to high acid comonomer contents. They contain a temperature stable ester that makes them functional in high-temperature coextrusions. They are available in pellet form for use in conventional extrusion and coextrusion equipment designed to process polyethylene (PE) resins. Applications: Bynel® Series 2000 resins can be used in a variety of coextrusion coating and laminating applications; for example, laminating metallized films to printed films. They can also be used in thermal lamination processes bonding to a variety of metal, plastic, and paper surfaces. Bynel® 2002, 2022, E403, and 20E482 adhere to a wide variety of materials. They are most often used in coextrusions with PE, EVA, polyamide, and ionomer. They are also useful in adhering to paper, foil, and printed films. Bynel® 2002 and 2022 are designed for low melt temperature coextrusion coating and laminating applications. Bynel® E403 has a melt index suitable for blown or cast film. The primary difference between Bynel® 2002, 2022, and E403 is their rheology. Bynel® 2014 adheres to a wide variety of materials. It is most often used to bond PP films to foil or metallized films. It is also useful in adhering to paper, PE, EVA, PP, and printed films. It has good draw properties and low neck-in, making it especially suited for processes such as coextrusion coating and laminating. It can also be used in film/sheet and tubing. Applications for which Bynel® 2014 is a good resin choice are snack packaging and non-retorted lidding structures in which metal barriers are combined with reverse-printed films. Physical properties of Bynel® Series 2000 resins are typical of ethylene/acrylate copolymer resins with similar density and melt index values. The rheology characteristics of each grade are different, so one may be better suited than the others to a particular extrusion process. Information provided by DuPont Packaging Polymers.

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_DuPont-Bynel-2022-Acid-Modified-Ethylene-Terpolymer-Adhesive-Resin.php](http://www.lookpolymers.com/polymer_DuPont-Bynel-2022-Acid-Modified-Ethylene-Terpolymer-Adhesive-Resin.php)

Physical Properties	Metric	English	Comments
Density	0.928 g/cc	0.0335 lb/in <sup>3</sup>	ASTM D792
Viscosity	200000 cP @Shear Rate 50.0 1/s, Temperature 190 °C	200000 cP @Shear Rate 50.0 1/s, Temperature 374 °F	estimated from log-log graph
Melt Flow	35 g/10 min @Load 2.16 kg, Temperature 190 °C	35 g/10 min @Load 4.76 lb, Temperature 374 °F	ASTM D1238

Thermal Properties	Metric	English	Comments
Melting Point	62.0 °C	144 °F	Freezing point via DSC/ASTM D3418
	87.0 °C	189 °F	Melting point via DSC/ASTM D3418
Vicat Softening Point	58.0 °C	136 °F	ASTM D1525

Processing Properties	Metric	English	Comments
Processing Temperature	275 °C	527 °F	Extruder forward zone and adapter.

Processing Properties	Metric	English	Comments
-----------------------	--------	---------	----------

## Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)

Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China