DuPont Bynel® 3095 Anhydride-Modified Ethylene Vinyl Acetate Adhesive Resin (discontinued **)

Category : Polymer , Thermoplastic , Ethylene Vinyl Acetate , Ethylene Vinyl Acetate Copolymer (EVA), Adhesive/Sealant Grade

Material Notes:

Bynel® Series 3000 resins are anhydride-modified ethylene vinyl acetate polymers. They are available in pellet form for use in conventional extrusion and coextrusion equipment designed to process polyethylene (PE) resins.Applications: Bynel® 3030, 3048, 3062, 3080, and 3095 adhere to a wide variety of materials. They are most often used to adhere to PE, ionomers, EVA, and polyamide. In addition, Bynel® 3062 also adheres to EVOH.Physical properties of Bynel® Series 3000 resins are typical of EVA resins with similar density and melt index values. The rheology characteristics of each grade are different, so one may be better suited than the others to a particular extrusion process. Information provided by DuPont Packaging Polymers.

Order this product through the following link:

http://www.lookpolymers.com/polymer_DuPont-Bynel-3095-Anhydride-Modified-Ethylene-Vinyl-Acetate-Adhesive-Resinnbspdiscontinued-.php

Physical Properties	Metric	English	Comments	
Density	0.925 g/cc	0.0334 lb/in³	ASTM D792	
Viscosity	800000 cP	800000 cP		
	@Shear Rate 50.0 1/s, Temperature 190 °C	@Shear Rate 50.0 1/s, Temperature 374 °F		
	2.3 g/10 min	2.3 g/10 min		
Melt Flow	@Load 2.16 kg, Temperature 190 °C	@Load 4.76 lb, Temperature 374 °F	ASTM D1238	

Thermal Properties	Metric	English	Comments
Melting Point	83.0 °C	181 °F	Freezing point via DSC/ASTM D3418
	102 °C	216 °F	Melting point via DSC/ASTM D3418
Vicat Softening Point	82.0 °C	180 °F	ASTM D1525

Processing Properties	Metric	English	Comments
Processing Temperature	235 °C	455 °F	Extruder forward zone and adapter. Degrades above 238°C.
Nozzle Temperature	235 °C	455 °F	Die

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com Email : sales@lookpolymers.com Tel : +86 021-51131842



Mobile : +86 13061808058 Skype : lookpolymers Address : United North Road 215,Fengxian District, Shanghai City,China