

DuPont Elvaloy® 1125 AC Ethylene and 25% Methyl Acrylate Copolymer

Category : Polymer , Film , Thermoplastic , Ethylene Methyl Acrylate , Ethylene-Methyl Acrylate Copolymer, Molding Grade

Material Notes:

Elvaloy® 1125 AC is intended for coextrusion and molding. It can be recommended for blow molding of parts requiring permanent flexibility, stress cracking resistance and softness. Excellent filler acceptance makes Elvaloy® 1125 AC suitable for highly filled compounds. Elvaloy® 1125 AC is easily processed on standard equipment used for low-density polyethylene. Information provided by DuPont.

Order this product through the following link:

http://www.lookpolymers.com/polymer_DuPont-Elvaloy-1125-AC-Ethylene-and-25-Methyl-Acrylate-Copolymer.php

Physical Properties	Metric	English	Comments
Density	0.944 g/cc	0.0341 lb/in ³	ASTM D792 - ISO 1183
Melt Flow	0.40 g/10 min @Load 2.16 kg, Temperature 190 °C	0.40 g/10 min @Load 4.76 lb, Temperature 374 °F	ASTM D1238 - ISO 1133

Mechanical Properties	Metric	English	Comments
Hardness, Shore A	78	78	ASTM D2240 - ISO 868
Hardness, Shore D	28	28	ASTM D2240 - ISO 868
Tensile Strength at Break	14.0 MPa	2030 psi	500 mm/min; ASTM D638 - ISO 527-2
Elongation at Break	760 %	760 %	500 mm/min; ASTM D638 - ISO 527-2
Tensile Modulus	0.0250 GPa	3.63 ksi	1 mm/min; ASTM D638 - ISO 527-2

Thermal Properties	Metric	English	Comments
Melting Point	90.0 °C	194 °F	By DSC; ASTM D3418 - ISO 3146
Vicat Softening Point	48.0 °C	118 °F	A ₅₀ (10N); ASTM D1525 - ISO 306

Processing Properties	Metric	English	Comments
Rear Barrel Temperature	150 °C	302 °F	Extrusion lamination
	150 °C	302 °F	Cast film
	150 °C	302 °F	Blown film
Middle Barrel Temperature	160 °C	320 °F	Blown film
	210 °C	410 °F	Cast film

Processing Properties	Metric	English	Comments
Front Barrel Temperature	170 °C	338 °F	Blown film
	250 °C	482 °F	Cast film
	290 °C	554 °F	Extrusion lamination
Adapter Temperature	180 °C	356 °F	Blown film
	250 °C	482 °F	Cast Film
	290 °C	554 °F	Extrusion lamination
Die Temperature	180 °C	356 °F	Blown film
	250 °C	482 °F	Cast film
	290 °C	554 °F	Extrusion lamination

Descriptive Properties	Value	Comments
MA-Content	25 wt. %	DuPont Method

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China