

## DuPont™ Elvax® 3190A Ethylene Vinyl Acetate

Category : Polymer , Thermoplastic , Ethylene Vinyl Acetate , Ethylene Vinyl Acetate Copolymer (EVA), Extrusion/Coating Grade

### Material Notes:

DuPont™ Elvax® 3190A is an extrudable ethylene-vinyl acetate copolymer resin available in pellet form for use in conventional extrusion equipment designed to process polyethylene resins. ELVAX® 3190A EVA Resin complies with Food and Drug Administration Regulation 21 CFR 177.1350(a)(1) - - Ethylene-vinyl acetate copolymers, subject to the limitations and requirements therein. This Regulation describes polymers that may be used in contact with food, subject to the finished food-contact article meeting the extractive limitations under the intended conditions of use, as shown in paragraph (b)(1) of the Regulation.

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_DuPont-Elvax-3190A-Ethylene-Vinyl-Acetate.php](http://www.lookpolymers.com/polymer_DuPont-Elvax-3190A-Ethylene-Vinyl-Acetate.php)

Physical Properties	Metric	English	Comments
Density	0.950 g/cc	0.0343 lb/in <sup>3</sup>	ASTM D792, ISO 1183
Melt Flow	2.0 g/10 min @Load 2.16 kg, Temperature 190 °C	2.0 g/10 min @Load 4.76 lb, Temperature 374 °F	ASTM D1238, ISO 1133

Thermal Properties	Metric	English	Comments
Melting Point	57.0 °C	135 °F	Freezing Point; ASTM D3418, ISO 3146
	80.0 °C	176 °F	ASTM D3418, ISO 3146
Vicat Softening Point	49.0 °C	120 °F	ASTM D1525, ISO 306

Processing Properties	Metric	English	Comments
Processing Temperature	<= 230 °C	<= 446 °F	
Melt Temperature	175 - 215 °C	347 - 419 °F	Blown/Cast Film Coextrusion

## Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)

Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China