

## DuPont™ Fusabond® E226 Polymer Modifier

Category : Polymer , Thermoplastic , Adhesives, Sealants, and Coatings

### Material Notes:

DuPont™ Fusabond® E226 is a anhydride modified polyethylene. Uses: Wire & Cable Applications Polymer Modifier Fusabond E226 resin conforms with the Code of Federal Regulations, Title 21, Paragraph 175.105, covering the use of adhesive interlayers in composite packages for food use. This regulation describes adhesives which may be safely used as components of articles intended for use in packaging, transporting or holding food. This regulation requires that either (1) the adhesive is separated from the food by a functional barrier, or (2) the quantity of adhesive which contacts fatty or aqueous foods does not exceed the trace amounts at the seams or edges.

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_DuPont-Fusabond-E226-Polymer-Modifier.php](http://www.lookpolymers.com/polymer_DuPont-Fusabond-E226-Polymer-Modifier.php)

Physical Properties	Metric	English	Comments
Density	0.930 g/cc	0.0336 lb/in <sup>3</sup>	ASTM D792, ISO 1183
Melt Flow	1.75 g/10 min @Load 2.16 kg, Temperature 190 °C	1.75 g/10 min @Load 4.76 lb, Temperature 374 °F	ASTM D1238, ISO 1133

Thermal Properties	Metric	English	Comments
Melting Point	102 °C	216 °F	Freezing Point; ASTM D3418
	120 °C	248 °F	ASTM D3418, ISO 3146
Vicat Softening Point	95.0 °C	203 °F	ASTM D1525, ISO 306

Processing Properties	Metric	English	Comments
Processing Temperature	<= 290 °C	<= 554 °F	

## Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)

Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China