

DuPont Nucrel® 2906 Ethylene-Methacrylic Acid Copolymer Resin (discontinued **)

Category : Polymer , Thermoplastic , Ethylene Methyl Acrylate

Material Notes:

Nucrel® 2906 is a tough, lightweight, easily processed ethylene copolymer resin. This resin is inherently flexible without the need for plasticizers. The resin can be pigmented, UV-stabilized for exterior applications and painted or plated for special decorative effects. Typical Applications: Heat sealable coatingBase resin for color concentratesMetal coatingDispersionsPaper coatingFeatures: Good adhesion to metal and many other polar substratesGood flow characteristics for compounding applicationsMay be processed into a dispersion through standard dispersion techniquesInformation provided by DuPont.

Order this product through the following link:

http://www.lookpolymers.com/polymer_DuPont-Nucrel-2906-Ethylene-Methacrylic-Acid-Copolymer-Resin-nbspdiscontinued-.php

Physical Properties	Metric	English	Comments
Density	0.950 g/cc	0.0343 lb/in ³	ASTM D792
Melt Index of Compound	60 g/10 min @Load 2.16 kg, Temperature 190 °C	60 g/10 min @Load 4.76 lb, Temperature 374 °F	ASTM D1238

Mechanical Properties	Metric	English	Comments
Hardness, Shore D	63	63	Initial (peak) hardness; ASTM D2240
Tensile Strength at Break	25.2 MPa	3650 psi	Type IV specimen, compression molded, crosshead speed 2 in/min; ASTM D638
Elongation at Break	451 %	451 %	Type IV specimen, compression molded, crosshead speed 2 in/min; ASTM D638
Flexural Modulus	0.0827 GPa	12.0 ksi	ASTM D790
Izod Impact, Notched	NB	NB	ASTM D256
Tensile Impact Strength	138.2 kJ/m ²	65.76 ft-lb/in ²	At 23°C; ASTM D1822S
	30.0 kJ/m ² @Temperature -40.0 °C	14.3 ft-lb/in ² @Temperature -40.0 °F	ASTM D1822S

Thermal Properties	Metric	English	Comments
Melting Point	56.0 - 83.0 °C	133 - 181 °F	ASTM D3418(DSC)
Vicat Softening Point	50.0 °C	122 °F	ASTM D1525

Processing Properties	Metric	English	Comments
Zone 1	160 °C	320 °F	
Zone 2	182 °C	360 °F	
Zone 3	193 °C	379 °F	
Zone 4	204 °C	399 °F	
Zone 5	204 °C	399 °F	
Die Temperature	204 °C	400 °F	
Melt Temperature	149 - 232 °C	300 - 450 °F	

Descriptive Properties	Value	Comments
Methacrylic Acid Content	19 wt. %	DuPont Method

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China