

## **DuPont Performance Polymers Hypalon® 40S Chlorosulfonated Polyethylene Rubber, General Description (discontin**

Category : Polymer , Thermoset , Rubber or Thermoset Elastomer (TSE) , Chlorosulfonated Polyethylene Rubber

## Material Notes:

Product form is white, odorless chips. Distinguishing Feature: Low viscosity polymer. Improves processing of dry stiff stocks.35 % Chlorine Content. 1% Sulfur Content. Excellent Abrasion Resistance. Excellent Chemical Resistance. Good Compression Set Resistance. Good Flame Resistance. Very Good Heat Resistance. Excellent Ozone Resistance. Good Petroleum Oil Resistance. Excellent Weather Resistance. Good Low Temperature Properties. Good Tear Strength.Processing: Excellent Extrusion. Excellent Molding. Excellent Calendering.Physical property data below (except viscosity and density) are for vulcanizate. MatWeb also has entries for various compounds of the Hypalon® grade.General Hypalon® Information: Vulcanizates of this chlorosulfonated polyethylene synthetic rubber are highly resistant to ozone, oxygen, weather, heat, oil, and chemicals. Hypalon resists discoloration on exposure to light and is widely used in light-colored vulcanizates. It can be compounded to give excellent mechanical properties. Several grades are available, all of which may be processed and used in the usual manner for solid elastomeric vulcanizates. Various grades of Hypalon have been used in single-ply roofing systems; auto power steering and oil cooler hoses; chemical-resistant liners; cable sheathing; and other coatings.Information provided by DuPont Dow Elastomers.This former DuPont Dow Elastomers product line is now produced by DuPont Performance Elastomers.

## Order this product through the following link:

http://www.lookpolymers.com/polymer\_DuPont-Performance-Polymers-Hypalon-40S-Chlorosulfonated-Polyethylene-Rubber-General-Description-nbspdiscontin.php

Physical Properties	Metric	English	Comments
Density	1.18 g/cc	0.0426 lb/in³	
Mooney Viscosity	46	46	ML 1 + 4; ASTM D1646-81
	@Temperature 100 °C	@Temperature 212 °F	

Mechanical Properties	Metric	English	Comments
Hardness, Shore A	40 - 95	40 - 95	ASTM D2240-81
Tensile Strength, Ultimate	<= 27.6 MPa	<= 4000 psi	With carbon black or gum stocks. ASTM D412-80

## Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com Email : sales@lookpolymers.com Tel : +86 021-51131842 Mobile : +86 13061808058 Skype : lookpolymers Address : United North Road 215,Fengxian District, Shanghai City,China