

DuPont Performance Polymers Neoprene NPR-9368 Polychloroprene (discontinued **)

Category: Polymer, Thermoset, Rubber or Thermoset Elastomer (TSE)

Material Notes:

Low viscosity polymer. Principal uses include: Difficult to bond substrates, PVD, PE, DIY, Footwear. Solids content: 49%. Initial pH: 12. Surface tension: 40 dyne/cm. Polymer type: Sol. Slow crystallization rate. Wet Gel Properties: Medium cure rate. Low modulus. General Neoprene Latex Information: Neoprene latexes are aqueous colloidal dispersions of polychloroprene or of copolymers of chloroprene with other monomers such as methacrylic acid or 2,3-dichloro-1,3-butadiene. They are available in both anionic and nonionic surfactant systems. All neoprene latexes have a unique combination of inherent characteristics including excellent film formation; high cohesive strength without curing; elastomeric properties over a wide temperature range; and considerable resistance to degradation from chemical or environmental exposure. Uses include adhesives, binders, coatings, dipped goods, elasticized asphalt and concrete, and foam. Information provided by DuPont Dow Elastomers. This former DuPont Dow Elastomers product line is now produced by DuPont Performance Elastomers. This grade is not a part of the standard product line.

Order this product through the following link:

http://www.lookpolymers.com/polymer_DuPont-Performance-Polymers-Neoprene-NPR-9368-Polychloroprene-nbspdiscontinued-.php

| Physical Properties | Metric | English | Comments |
|---------------------|-----------|---------------|----------|
| Density | 1.10 g/cc | 0.0397 lb/in³ | Latex |
| | 1.23 g/cc | 0.0444 lb/in³ | Polymer |

Contact Songhan Plastic Technology Co.,Ltd.

Website: www.lookpolymers.com Email: sales@lookpolymers.com

Tel: +86 021-51131842 Mobile: +86 13061808058

Skype: lookpolymers

Address: United North Road 215, Fengxian District, Shanghai City, China

uuless . Oliiteu Nortii noau 213,Feriyxiaii District, Silaliyilai Gity,Gililla