

## DuPont™ Scclairfilm® SL-3 LLDPE Film, Laminating, 50.8 µm Thickness (discontinued \*\*)

Category : Polymer , Film , Thermoplastic , Polyethylene (PE) , LLDPE , Linear Low Density Polyethylene (LLDPE), Film Grade

### Material Notes:

Data provided by DuPont Packaging Polymers.SL is a linear low density polyolefin film which offers a combination of toughness and durability plus outstanding clarity. These have superior tensile strength, puncture strength, elongation and heat seal strength compared to conventional films. Ideal for lamination to other substrates such as Dartek nylon film or Mylar polyester film for vacuum packaging applications. SL, in converter combinations, is particularly suited for the vacuum packaging of processed meats.

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_DuPont-Scclairfilm-SL-3-LLDPE-Film-Laminating-508-m-Thickness-nbspdiscontinued-.php](http://www.lookpolymers.com/polymer_DuPont-Scclairfilm-SL-3-LLDPE-Film-Laminating-508-m-Thickness-nbspdiscontinued-.php)

Physical Properties	Metric	English	Comments
Density	0.918 g/cc	0.0332 lb/in <sup>3</sup>	
Moisture Vapor Transmission	0.470 cc-mm/m <sup>2</sup> -24hr-atm	1.19 cc-mil/100 in <sup>2</sup> -24hr-atm	ASTM E96 Procedure E
Water Vapor Transmission	9.30 g/m <sup>2</sup> /day @Temperature 38.0 °C	0.599 g/100 in <sup>2</sup> /day @Temperature 100 °F	ASTM E96 Procedure E
Oxygen Transmission	198 cc-mm/m <sup>2</sup> -24hr-atm	503 cc-mil/100 in <sup>2</sup> -24hr-atm	or 3900 cc/m <sup>2</sup> -24hr-atm for the film. ASTM D3985

Mechanical Properties	Metric	English	Comments
Film Elongation at Break, MD	600 %	600 %	ASTM D882
Tensile Modulus	0.170 GPa	24.7 ksi	ASTM D882
Dart Drop Test	125 g	0.276 lb	
Seal Strength	>= 2000 g/25 mm	>= 2000 g/in	Sentinel Sealer Test
Film Tensile Strength at Break, MD	34.0 MPa	4930 psi	ASTM D882

Optical Properties	Metric	English	Comments
Haze	9.0 %	9.0 %	ASTM D1003
Gloss	100 %	100 %	20°; ASTM D2457

## Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)

Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215, Fengxian District, Shanghai City, China