

## DuPont™ Tedlar® TUT10BG3 UV Screening Transparent Polyvinyl Fluoride Film

Category : Polymer , Film , Thermoplastic , Fluoropolymer

### Material Notes:

Properties of DuPont™ Tedlar® polyvinyl fluoride (PVF) biaxially oriented film include excellent resistance to weathering, outstanding mechanical properties, and inertness towards a wide variety of chemicals, solvents, and staining agents. Information provided by DuPont.

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_DuPont-Tedlar-TUT10BG3-UV-Screening-Transparent-Polyvinyl-Fluoride-Film.php](http://www.lookpolymers.com/polymer_DuPont-Tedlar-TUT10BG3-UV-Screening-Transparent-Polyvinyl-Fluoride-Film.php)

Physical Properties	Metric	English	Comments
Specific Gravity	1.37 g/cc	1.37 g/cc	ASTM D1505
Moisture Absorption at Equilibrium	<= 0.50 %	<= 0.50 %	ASTM D570
Moisture Vapor Transmission	0.760 cc-mm/m <sup>2</sup> -24hr-atm	1.93 cc-mil/100 in <sup>2</sup> -24hr-atm	ASTM E96
Thickness	25.4 microns	1.00 mil	

Mechanical Properties	Metric	English	Comments
Film Elongation at Break, MD	>= 95 %	>= 95 %	ASTM D882
Secant Modulus, MD	2.14 GPa	310 ksi	ASTM D822
Impact	90.3	90.3	kJ/m; Spencer; ASTM D3420
Coefficient of Friction	0.21	0.21	Film: Metal; ASTM D1894
Tear Strength	144 kN/m	822 pli	Graves (initial), MD; ASTM D1004
	168 kN/m	959 pli	Graves (initial), TD; ASTM D1004
Elmendorf Tear Strength, MD	0.673 g/micron	17.1 g/mil	ASTM D1922
Elmendorf Tear Strength, TD	0.748 g/micron	19.0 g/mil	ASTM D1922
Film Tensile Strength at Break, MD	>= 89.6 MPa	>= 13000 psi	ASTM D882

Thermal Properties	Metric	English	Comments
CTE, linear	78.0 µm/m-°C	43.3 µin/in-°F	MD; ASTM D696
	@Temperature 50.0 - 70.0 °C	@Temperature 122 - 158 °F	
	81.0 µm/m-°C	45.0 µin/in-°F	TD; ASTM D696
	@Temperature 50.0 - 70.0 °C	@Temperature 122 - 158 °F	

Specific Heat Capacity Thermal Properties	1.76 J/g·°C Metric	0.421 BTU/lb·°F English	DuPont 990 test Comments
Maximum Service Temperature, Air	107 °C	225 °F	Continuous
	175 °C	347 °F	Short Cycle
Minimum Service Temperature, Air	-72.0 °C	-97.6 °F	Continuous
Shrinkage	<= 6.0 % @Temperature 170 °C	<= 6.0 % @Temperature 338 °F	TD; ASTM D1204

Optical Properties	Metric	English	Comments
Refractive Index	1.46 @Temperature 30.0 °C	1.46 @Temperature 86.0 °F	n <sub>D</sub> ; Abbe Refractometer; ASTM D-542
Transmission, Visible	90 %	90 %	transparent; thickness not quantified

Descriptive Properties	Value	Comments
Aging in Air	> 3000 hours to embrittlement	300°F Oven

## Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)

Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China