

## DuPont Teijin Films Mylar® EL Polyester Film, 200 Gauge

Category : Polymer , Film , Thermoplastic , Polyester, TP , Polyester Film

### Material Notes:

Mylar® EL films, typically 48 through 500 gauge are strong, tough, general -purpose films for electrical/electronic uses. Heavier gauges of Mylar® EL films are similar to Mylar® MO films. Available in grades from clear to hazy, Mylar® EL films offer chemical inertness, good dielectrics, high temperature durability, and good handling characteristics. General Product Info: The superior electrical, mechanical, thermal, and chemical inertness characteristics of Mylar® type EL films make them ideally suited for electrical and electronic applications. Typical Applications: The outstanding strength, flexibility, and electrical properties of Mylar® type EL films make them well suited for many electrical and electronics applications. The good handling and winding characteristics make them especially suitable for coating, die cutting, embossing, and laminating operations. Approvals: UL 94 VTM-2 - for 92 - 500 gauge (0.023 - 0.13mm) Information provided by DuPont.

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_DuPont-Teijin-Films-Mylar-EL-Polyester-Film-200-Gauge.php](http://www.lookpolymers.com/polymer_DuPont-Teijin-Films-Mylar-EL-Polyester-Film-200-Gauge.php)

| Physical Properties | Metric    | English                   | Comments                   |
|---------------------|-----------|---------------------------|----------------------------|
| Density             | 1.39 g/cc | 0.0502 lb/in <sup>3</sup> | Typical Mylar®; ASTM D1505 |

| Mechanical Properties              | Metric  | English   | Comments   |
|------------------------------------|---------|-----------|------------|
| Film Elongation at Break, MD       | 135 %   | 135 %     | ASTM D882A |
| Film Elongation at Break, TD       | 110 %   | 110 %     | ASTM D882A |
| Film Tensile Strength at Break, MD | 193 MPa | 28000 psi | ASTM D882A |
| Film Tensile Strength at Break, TD | 228 MPa | 33000 psi | ASTM D882A |

| Thermal Properties     | Metric  | English   | Comments               |
|------------------------|---|---|------------------------|
| Specific Heat Capacity | 1.17 J/g-°C                                     | 0.280 BTU/lb-°F                                   | Typical Mylar®         |
| Melting Point          | 254 °C  | 489 °F  | Typical Mylar® via DSC |
| Shrinkage, MD          | 1.3 %<br>@Temperature 150 °C,<br>Time 1800 sec  | 1.3 %<br>@Temperature 302 °F,<br>Time 0.500 hour  | Unrestrained           |
| Shrinkage, TD          | 0.80 %<br>@Temperature 150 °C,<br>Time 1800 sec | 0.80 %<br>@Temperature 302 °F,<br>Time 0.500 hour | Unrestrained           |

| Optical Properties | Metric      | English     | Comments          |
|--------------------|-------------|-------------|-------------------|
| Refractive Index   | 1.64 - 1.67 | 1.64 - 1.67 | typical of Mylar® |

| Haze<br>Optical Properties | 24 %<br>Metric | 24 %<br>English | ASTM D1003<br>Comments |
|----------------------------|----------------|-----------------|------------------------|
|----------------------------|----------------|-----------------|------------------------|

| Electrical Properties | Metric    | English    | Comments   |
|-----------------------|-----------|------------|--|
| Dielectric Strength   | 152 kV/mm | 3850 kV/in | 1/4" electrode 500 V/sec 25°C in air;<br>ASTM D149 |
| Dielectric Breakdown  | 7700 V    | 7700 V     | 1/4" electrode 500 V/sec 25°C in air;<br>ASTM D149 |

| Descriptive Properties | Value                    | Comments |
|------------------------|--------------------------|----------|
| Yield (nominal)        | 9900 in <sup>2</sup> /lb |          |

## Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)

Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China