

## DuPont Teijin Films Mylar® MDA Polyester Film, 200 Gauge

Category : Polymer , Film , Thermoplastic , Polyester, TP , Polyester Film

### Material Notes:

Mylar® MDA films are tough, general purpose films that are transparent in 48 through 92 gauge and translucent in heavier gauges. They have a rough surface to provide ease of handling, good adhesion, and processability. They are used for a broad range of industrial applications and may be suitable for use in medical applications. General Product Info: Mylar® MDA films have balanced tensile properties and excellent resistance to moisture and most chemicals. They can withstand temperature extremes from -100°F to 300°F. Mylar® does not become brittle with age under normal conditions, because it contains no plasticizers. Typical Applications: Apparel stays Book jackets Carbon ribbon Control Tape Drumheads Duct Liners Identifications Medical Applications Membrane touch switches Metallized Base Pressure Sensitive Labels (plain or metallized) Protective surfacing Release liners Roll leaf (hot stamping) Spirit Masters Approvals: FDA Food Contact Status - All gauges of Mylar® MDA comply with the Food and Drug Administration regulation 21 CFR 177.1630 -- Polyethylene phthalate polymers. This regulation describes films which may be safely used in contact with all types of food excluding alcoholic beverages. Uncoated films such as Mylar® MDA can be used to contain foods during oven cooking or oven baking at temperatures above 250 °F. Information provided by DuPont.

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_DuPont-Teijin-Films-Mylar-MDA-Polyester-Film-200-Gauge.php](http://www.lookpolymers.com/polymer_DuPont-Teijin-Films-Mylar-MDA-Polyester-Film-200-Gauge.php)

Physical Properties	Metric	English	Comments
Density	1.39 g/cc	0.0502 lb/in <sup>3</sup>	Typical Mylar®; ASTM D1505

Mechanical Properties	Metric	English	Comments
Film Elongation at Break, MD	135 %	135 %	ASTM D882A
Film Elongation at Break, TD	110 %	110 %	ASTM D882A
Tensile Modulus	3.50 GPa	507 ksi	ASTM D882
Film Tensile Strength at Break, MD	193 MPa	28000 psi	ASTM D882A
Film Tensile Strength at Break, TD	228 MPa	33000 psi	ASTM D882A

Thermal Properties	Metric	English	Comments
Specific Heat Capacity	1.17 J/g-°C	0.280 BTU/lb-°F	Typical Mylar®
Melting Point	254 °C	489 °F	Typical Mylar® via DSC
Maximum Service Temperature, Air	149 °C	300 °F	
Maximum Service Temperature, Inert	-73.3 °C	-100 °F	
Shrinkage, MD	1.3 % @Temperature 150 °C, Time 1800 sec	1.3 % @Temperature 302 °F, Time 0.500 hour	Unrestrained

Thermal Properties	Metric	English	Comments
Shrinkage, TD	@Temperature 150 °C, Time 1800 sec	@Temperature 302 °F, Time 0.500 hour	Unrestrained

Optical Properties	Metric	English	Comments
Refractive Index	1.64 - 1.67	1.64 - 1.67	typical of Mylar®
Haze	13 - 37 %	13 - 37 %	ASTM D1003

Descriptive Properties	Value	Comments
Yield (nominal)	9900 in <sup>2</sup> /lb	

## Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)

Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China