

Dyna-Purge[®] B Purging Compound

Category : Polymer , Thermoplastic , Purging Compound

Material Notes:

Designed for Injection and Extrusion Blow Molding
General Description: DYNA-PURGE B is a non-abrasive, non-chemical "engineered" thermoplastic purging compound, formulated to flow naturally through the barrel and accumulator head. A non-melting but softening thermoplastic scrubs the screw and barrel, while the carrier matrix flushes away impurities.
FEATURES & BENEFITS OF DYNA-PURGE B
 Excellent for color changes, resin changes, preventative machine maintenance, and before manual cleaning
 Developed for purging through the barrel and die head with a minimum clearance of .025 inch (.65 mm)
 Effective through a wide temperature range 320°F-575°F (160°C-302°C)
 Easy to use " no process adjustment necessary " use at the resident resin processing temperature and RPM speed
 Non-abrasive, non-melting but softening thermoplastic, which thoroughly loosens carbonized and degraded resin, allowing it to be flushed out of the system
 Safe, non-hazardous, with no chemicals " ingredients are FDA compliant
 Heat stable " recommended during shutdown and start-up
 Low "cost-per-purge" " only small quantity needed to be effective
 No mixing required " simply use "as is"
 Unlimited shelf life

Order this product through the following link:

http://www.lookpolymers.com/polymer_Dyna-Purge-B-Purging-Compound.php

Processing Properties	Metric	English	Comments
Processing Temperature	160 - 302 °C	320 - 576 °F	Injection
	160 - 302 °C	320 - 576 °F	Extrusion

Descriptive Properties	Value	Comments
Amount of Purge (Extrusion)	Approx. 10 lbs per diameter inch of screw	L:D dependant
Amount of Purge (Injection)	Approx. 2 lbs per diameter inch of screw	
Minimum Orifice (Extrusion)	.025in, .65mm	Die
Minimum Orifice (Injection)	.025in, .65mm	Nozzle
Screen Packs or other flow restrictions (Ext.)	Combination of 20, 40, 60 or 80 mesh; 100 or more, use SF or F	
Screen Packs or other flow restrictions (Inj.)	Must have minimum clearance of .025in (.65mm)	
Types of Resins	All	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China