

## ELASTO UK Dryflex® 500900S SEBS Based Material, Unfilled Qualities, 90A Hardness, Translucent

Category : Polymer , Thermoplastic , Elastomer, TPE , Thermoplastic Elastomer, Melt-Processible Rubber

### Material Notes:

The 500-series is very favorable when transparency and good scratch resistance are required, as well as when there are high surface finish requirements. Unfilled grades have excellent flow and mechanical properties, such as elongation, compression set, tensile and tear strength. The low density entails lower weight compared to the 600 and 660-series. Information from Vita Thermoplastic Polymers (VTP). Vita Thermoplastic Polymers was acquired by HEXPOL and is now ELASTO

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_ELASTO-UK-Dryflex-500900S-SEBS-Based-Material-Unfilled-Qualities-90A-Hardness-Translucent.php](http://www.lookpolymers.com/polymer_ELASTO-UK-Dryflex-500900S-SEBS-Based-Material-Unfilled-Qualities-90A-Hardness-Translucent.php)

Physical Properties	Metric	English	Comments
Specific Gravity	0.890 g/cc	0.890 g/cc	ASTM D792
Linear Mold Shrinkage	0.0080 - 0.020 cm/cm	0.0080 - 0.020 in/in	
Melt Flow	3.0 g/10 min @Load 2.16 kg, Temperature 190 °C	3.0 g/10 min @Load 4.76 lb, Temperature 374 °F	ASTM D1238

Mechanical Properties	Metric	English	Comments
Hardness, Shore A	90 @Thickness 4.00 mm	90 @Thickness 0.157 in	ASTM D2240
Tensile Strength at Break	14.0 MPa	2030 psi	ASTM D638
Elongation at Break	>= 600 %	>= 600 %	ASTM D638
100% Modulus	0.00600 GPa	0.870 ksi	ASTM D638
300% Modulus	0.00700 GPa	1.02 ksi	ASTM D638
Tear Strength	60.0 kN/m	342 pli	ASTM D624
Compression Set	30 %	30 %	at 23°C, 72 hrs; ASTM D395

Thermal Properties	Metric	English	Comments
Maximum Service Temperature, Air	125 °C	257 °F	
Minimum Service Temperature, Air	-50.0 °C	-58.0 °F	

Processing Properties	Metric	English	Comments
-----------------------	--------	---------	----------

Processing Temperature Processing Properties	180 - 210 °C Metric	356 - 410 °F English	Comments
Descriptive Properties	Value	Comments	
Bonding to PP	Excellent		
Chemical Resistance	Good	Excluding organic solvents, aromatic and vegetable oils	
Color	Translucent		
Weather Resistance	Excellent	Air ageing	

## Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)

Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China