

ELASTO UK Dryflex® 502650S SEBS Based Material, Unfilled Qualities, 65A Hardness, Black

Category : Polymer , Thermoplastic , Elastomer, TPE , Thermoplastic Elastomer, Melt-Processible Rubber

Material Notes:

The 500-series is very favorable when transparency and good scratch resistance are required, as well as when there are high surface finish requirements. Unfilled grades have excellent flow and mechanical properties, such as elongation, compression set, tensile and tear strength. The low density entails lower weight compared to the 600 and 660-series. Information from Vita Thermoplastic Polymers (VTP). Vita Thermoplastic Polymers was acquired by HEXPOL and is now ELASTO

Order this product through the following link:

http://www.lookpolymers.com/polymer_ELASTO-UK-Dryflex-502650S-SEBS-Based-Material-Unfilled-Qualities-65A-Hardness-Black.php

Physical Properties	Metric	English	Comments
Specific Gravity	0.890 g/cc	0.890 g/cc	ASTM D792
Linear Mold Shrinkage	0.0080 - 0.020 cm/cm	0.0080 - 0.020 in/in	
Melt Flow	2.0 g/10 min @Load 2.16 kg, Temperature 190 °C	2.0 g/10 min @Load 4.76 lb, Temperature 374 °F	ASTM D1238

Mechanical Properties	Metric	English	Comments
Hardness, Shore A	65 @Thickness 4.00 mm	65 @Thickness 0.157 in	ASTM D2240
Tensile Strength at Break	8.00 MPa	1160 psi	ASTM D638
Elongation at Break	>= 600 %	>= 600 %	ASTM D638
100% Modulus	0.00200 GPa	0.290 ksi	ASTM D638
300% Modulus	0.00300 GPa	0.435 ksi	ASTM D638
Tear Strength	28.0 kN/m	160 pli	ASTM D624
Compression Set	20 %	20 %	at 23°C, 72 hrs; ASTM D395

Thermal Properties	Metric	English	Comments
Maximum Service Temperature, Air	125 °C	257 °F	
Minimum Service Temperature, Air	-50.0 °C	-58.0 °F	

Processing Properties	Metric	English	Comments
Processing Temperature	180 - 210 °C	356 - 410 °F	

Processing Properties	Metric	English	Comments
Descriptive Properties	Value	Comments	
Bonding to PP	Excellent		
Chemical Resistance	Good	Excluding organic solvents, aromatic and vegetable oils	
Color	Black		
Weather Resistance	Excellent	Air ageing	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China