

ELASTO UK Dryflex® 600750S SEBS Based Material, Filled Qualities, 75A Hardness, Natural

Category: Polymer, Thermoplastic, Elastomer, TPE, Thermoplastic Elastomer, Melt-Processible Rubber

Material Notes:

The most significant features of the 600-series are the improved heat stability, the sound reduction and that the material enables an easy and secure pigmenting for the customer. A filled material reduced that stickiness and sink marks on thick details but has limited scratch resistance. Information from Vita Thermoplastic Polymers (VTP). Vita Thermoplastic Polymers was aquired by HEXPOL and is now ELASTO

Order this product through the following link:

http://www.lookpolymers.com/polymer_ELASTO-UK-Dryflex-600750S-SEBS-Based-Material-Filled-Qualities-75A-Hardness-Natural.php

Physical Properties	Metric English Comments		Comments
Specific Gravity	1.16 g/cc	1.16 g/cc ASTM D792	
Linear Mold Shrinkage	0.0080 - 0.020 cm/cm	0.0080 - 0.020 in/in	
Melt Flow	5.0 g/10 min	5.0 g/10 min	
	@Load 5.00 kg, Temperature 190 °C	@Load 11.0 lb, Temperature 374 °F	ASTM D1238

Mechanical Properties	Metric English		Comments	
Hardness, Shore A	75	75	ASTM D2240	
	@Thickness 4.00 mm	@Thickness 0.157 in		
Tensile Strength at Break	9.00 MPa	1310 psi	ASTM D638	
Elongation at Break	>= 600 %	>= 600 %	ASTM D638	
100% Modulus	0.00300 GPa	0.435 ksi	ASTM D638	
300% Modulus	0.00400 GPa	0.580 ksi	ASTM D638	
Tear Strength	33.0 kN/m	188 pli	ASTM D624	
Compression Set	27 % 27 % at 23°C, 72 hrs; ASTM		at 23°C, 72 hrs; ASTM D395	

Thermal Properties	Metric	English	Comments
Maximum Service Temperature, Air	125 °C	257 °F	
Minimum Service Temperature, Air	-50.0 °C	-58.0 °F	

Processing Properties	Metric	English	Comments
Processing Temperature	180 - 210 °C	356 - 410 °F	



Descriptive Properties	Value	Comments
Bonding to PP	Excellent	
Chemical Resistance	Good	Excluding organic solvents, aromatic and vegetable oils
Color	Natural	
Weather Resistance	Excellent	Air ageing

Contact Songhan Plastic Technology Co.,Ltd.

Website: www.lookpolymers.com Email: sales@lookpolymers.com

Tel: +86 021-51131842 Mobile: +86 13061808058 Skype: lookpolymers

Address: United North Road 215, Fengxian District, Shanghai City, China