

**EMS-Griltech Griltech® 9E Copolyester Hotmelt Adhesive (Apparel Interlinings)**

Category : Polymer , Adhesive , Thermoplastic , Polyester , TP

**Material Notes:**

Description: GRILTEX adhesive products, either in pellet or powdered form, are used to coat apparel interlining substrates. Interlining substrates, coated with GRILTEX adhesive products, provides for excellent resistance and dimensional stability of the finished garment. For technical applications, GRILTEX adhesive products are used to optimize the manufacturing process for the production of automotive interior components or parts for other applications. All values were determined on dried pellets. Main Application System: Paste Dot, Powder Dot, Scatter Coating, Hotmelt Main Usage: Men's and Children's Wear, Women's Wear, Leisure and Sports Wear Data provided by EMS-Griltech.

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_EMS-Griltech-Griltech-9E-Copolyester-Hotmelt-Adhesive-Apparel-Interlinings.php](http://www.lookpolymers.com/polymer_EMS-Griltech-Griltech-9E-Copolyester-Hotmelt-Adhesive-Apparel-Interlinings.php)

Physical Properties	Metric	English	Comments
Viscosity	350000 cP	350000 cP	2.16 kg load; ISO 1133
	@Temperature 160 °C	@Temperature 320 °F	
Melt Flow	30 g/10 min	30 g/10 min	cm <sup>3</sup> /10 min; ISO 1133
	@Load 2.16 kg, Temperature 160 °C	@Load 4.76 lb, Temperature 320 °F	

Thermal Properties	Metric	English	Comments
Melting Point	118 - 123 °C	244 - 253 °F	DSC
Maximum Service Temperature, Air	<= 75.0 °C	<= 167 °F	Laundering Resistance

Processing Properties	Metric	English	Comments
Processing Temperature	120 - 150 °C	248 - 302 °F	Glue Line Temperature
Roll Temperature	50.0 - 65.0 °C	122 - 149 °F	Temperature of Engraved Rolls

Descriptive Properties	Value	Comments
Dry Cleaning Resistance	Good	
Steam Resistance	Good	

**Contact Songhan Plastic Technology Co.,Ltd.**

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215, Fengxian District, Shanghai City, China