

EMS-Grivory Grivory® 2D 25 W 20 X nat PA612-I

Category : Polymer , Thermoplastic , Nylon , Nylon 612

Material Notes:

Product Description: Grilamid 2D 25 W 20 X natural 9992 is a semi-flexible high viscosity, plasticized, high impact, heat and UV resistant extrusion grade based on polyamide 612 (PA612). Unique properties of Grilamid 2D 25 W 20 X natural 9992 are: High strength, high burst pressure in tube form Good heat resistance Significantly lower water absorption compared to standard polyamides Good chemical and hydrolysis resistance Low density Easy processing Application examples: Grilamid 2D 25 W 20 X natural 9992 has been developed especially for media lines in passenger cars and trucks. Thanks to its excellent resistance it is particularly suitable for fuel, diesel, air brake, oil, cooling fluid or hydraulic tubes. Information provided by EMS Grivory

Order this product through the following link:

http://www.lookpolymers.com/polymer_EMS-Grivory-Grivory-2D-25-W-20-X-nat-PA612-I.php

Physical Properties	Metric	English	Comments
Density	1.04 g/cc	0.0376 lb/in ³	ISO 1183
Water Absorption	2.1 %	2.1 %	ISO 62
Moisture Absorption	0.900 %	0.900 %	ISO 62

Mechanical Properties	Metric	English	Comments
Ball Indentation Hardness	30.0 MPa	4350 psi	conditioned; ISO 2039-1
	39.0 MPa	5660 psi	dry; ISO 2039-1
Tensile Stress	25.0 MPa	3630 psi	conditioned; ISO 527-1/-2
	@Strain 50.0 %	@Strain 50.0 %	
Elongation at Break	30.0 MPa	4350 psi	dry; ISO 527-1/-2
	@Strain 50.0 %	@Strain 50.0 %	
Tensile Modulus	>= 50 %	>= 50 %	dry; ISO 527-1/-2
	>= 50 %	>= 50 %	conditioned; ISO 527-1/-2
Charpy Impact Unnotched	0.400 GPa	58.0 ksi	conditioned; ISO 527-1/-2
	0.600 GPa	87.0 ksi	dry; ISO 527-1/-2
Charpy Impact Unnotched	NB	NB	dry; ISO 179/1eU
	NB	NB	conditioned; ISO 179/1eU
	NB	NB	dry; ISO 179/1eU
	@Temperature 30.0 °C	@Temperature 86.0 °F	

Mechanical Properties	NB Metric	NB English	Comments
	@Temperature 30.0 °C	@Temperature 86.0 °F	
Charpy Impact, Notched	NB	NB	dry; ISO 179/1eA
	NB	NB	conditioned; ISO 179/1eA
	1.30 J/cm ²	6.19 ft-lb/in ²	conditioned; ISO 179/1eU
	@Temperature 30.0 °C	@Temperature 86.0 °F	
	1.50 J/cm ²	7.14 ft-lb/in ²	dry; ISO 179/1eU
	@Temperature 30.0 °C	@Temperature 86.0 °F	

Thermal Properties	Metric	English	Comments
CTE, linear, Parallel to Flow	200 µm/m-°C	111 µin/in-°F	ISO 11359-1/-2
CTE, linear, Transverse to Flow	120 µm/m-°C	66.7 µin/in-°F	ISO 11359-1/-2
Melting Point	210 °C	410 °F	10°C/min; ISO 11357-1/-3
Deflection Temperature at 0.46 MPa (66 psi)	115 °C	239 °F	ISO 75-1/-2
Deflection Temperature at 1.8 MPa (264 psi)	50.0 °C	122 °F	ISO 75-1/-2
Flammability, UL94	HB	HB	IEC 60695-11-10

Electrical Properties	Metric	English	Comments
Volume Resistivity	1.00e+10 ohm-cm	1.00e+10 ohm-cm	dry; IEC 60093
	1.00e+10 ohm-cm	1.00e+10 ohm-cm	conditioned; IEC 60093
Surface Resistance	1.00e+10 ohm	1.00e+10 ohm	IEC 60093
Dielectric Strength	37.0 kV/mm	940 kV/in	dry; IEC 60243-1
	37.0 kV/mm	940 kV/in	conditioned; IEC 60243-1
Comparative Tracking Index	600 V	600 V	conditioned; IEC 60112

Descriptive Properties	Value	Comments
Additives	Plasticizer	
Automotive	Air intake systems	
	Compressed air systems	
	Cooling and climate control	

Descriptive Properties	Value systems	Comments
	Hydraulic systems	
	Powertrain and Chassis	
Electricals & Electronics	Cables & Tubes	
Form	Granules	
Industry & Consumer goods	Hydraulics & Pneumatics	
	Mechanical Engineering	
Processing	Other Extrusion	
	Profile Extrusion	
Product Attributes	Flexible	
	High viscosity	
	Hydrolysis resistant	
Special Characteristics	High impact or impact modified	
	Improved heat resistance	
	Light stabilized or stable to light	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China