

EMS-Grivory Grivory® BG-30 S FA PA6-GF30

Category : Polymer , Thermoplastic , Nylon , Nylon 6 , Nylon 6 , 30% Glass Fiber Filled

Material Notes:

Product description: Grilon BG-30 S FA is a heat stabilized PA6 injection molding grade with 30% glass fibers. Grilon BG-30 S FA has the following important properties: Excellent surface finish Easy flowing Easy processing Satisfies the EEC guidelines for materials in contact with foodstuffs The special stabilizing system of Grilon BG- 30 S FA allows the usage in direct contact with foodstuffs. Application examples are domestic appliances and requisites in direct contact with foodstuffs. Information provided by EMS Grivory

Order this product through the following link:

http://www.lookpolymers.com/polymer_EMS-Grivory-Grivory-BG-30-S-FA-PA6-GF30.php

Physical Properties	Metric	English	Comments
Density	1.35 g/cc	0.0488 lb/in ³	ISO 1183
Water Absorption	7.0 %	7.0 %	ISO 62
Moisture Absorption	2.00 %	2.00 %	ISO 62
Linear Mold Shrinkage, Flow	0.0010 cm/cm	0.0010 in/in	ISO 294-4, 2577
Linear Mold Shrinkage, Transverse	0.0060 cm/cm	0.0060 in/in	ISO 294-4, 2577

Mechanical Properties	Metric	English	Comments
Ball Indentation Hardness	100 MPa	14500 psi	conditioned; ISO 2039-1
	210 MPa	30500 psi	dry; ISO 2039-1
Tensile Strength at Break	125 MPa	18100 psi	conditioned; ISO 527-1/-2
	185 MPa	26800 psi	dry; ISO 527-1/-2
Elongation at Break	4.0 %	4.0 %	dry; ISO 527-1/-2
	10 %	10 %	conditioned; ISO 527-1/-2
Tensile Modulus	6.00 GPa	870 ksi	conditioned; ISO 527-1/-2
	9.50 GPa	1380 ksi	dry; ISO 527-1/-2
Charpy Impact Unnotched	8.50 J/cm ²	40.4 ft-lb/in ²	dry; ISO 179/1eU
	9.00 J/cm ²	42.8 ft-lb/in ²	conditioned; ISO 179/1eU
	7.00 J/cm ²	33.3 ft-lb/in ²	dry; ISO 179/1eU
	@Temperature 30.0 °C	@Temperature 86.0 °F	
	7.00 J/cm ²	33.3 ft-lb/in ²	conditioned; ISO 179/1eU

Mechanical Properties	@Temperature 30.0 °C Metric	@Temperature 86.0 °F English	Comments
Charpy Impact, Notched	1.10 J/cm ²	5.23 ft-lb/in ²	dry; ISO 179/1eA
	2.00 J/cm ²	9.52 ft-lb/in ²	conditioned; ISO 179/1eA
	0.800 J/cm ²	3.81 ft-lb/in ²	dry; ISO 179/1eU
	@Temperature 30.0 °C	@Temperature 86.0 °F	
	0.900 J/cm ²	4.28 ft-lb/in ²	conditioned; ISO 179/1eU
	@Temperature 30.0 °C	@Temperature 86.0 °F	

Thermal Properties	Metric	English	Comments
CTE, linear, Parallel to Flow	20.0 µm/m-°C	11.1 µin/in-°F	ISO 11359-1/-2
CTE, linear, Transverse to Flow	110 µm/m-°C	61.1 µin/in-°F	ISO 11359-1/-2
Melting Point	222 °C	432 °F	10°C/min; ISO 11357-1/-3
Maximum Service Temperature, Air	100 - 120 °C	212 - 248 °F	long term; EMS
	200 °C	392 °F	short term; EMS
Deflection Temperature at 1.8 MPa (264 psi)	205 °C	401 °F	ISO 75-1/-2
Deflection Temperature at 8.0 MPa	135 °C	275 °F	ISO 75-1/-2
Flammability, UL94	HB	HB	IEC 60695-11-10

Electrical Properties	Metric	English	Comments
Volume Resistivity	1.00e+13 ohm-cm	1.00e+13 ohm-cm	conditioned; IEC 60093
	1.00e+14 ohm-cm	1.00e+14 ohm-cm	dry; IEC 60093
Surface Resistance	1.00e+12 ohm	1.00e+12 ohm	IEC 60093
Dielectric Strength	37.0 kV/mm	940 kV/in	conditioned; IEC 60243-1
	40.0 kV/mm	1020 kV/in	dry; IEC 60243-1
Comparative Tracking Index	500 V	500 V	conditioned; IEC 60112

Descriptive Properties	Value	Comments
Automotive	Air intake systems	
	Interior	
Electricals & Electronics	Electrical appliances	

Descriptive Properties	Value	Comments
Food contact	EU Requirements	
	FDA	
Form	Granules	
Industry & Consumer goods	Housewares	
	Sports & Leisure	
Packaging	Medical packaging	
Processing	Injection Molding	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China