

## EMS-Grivory Grivory® CF 7 PA\*

Category : Polymer , Thermoplastic , Nylon

### Material Notes:

Product description Grilon CF 7 is a Copolyamide. Good flexibility and toughness Good thermoforming and orientation properties Good shrink characteristics Good transparency Reduced melting point Grilon CF 7 is suitable for the manufacture of both cast and blown films. It is suitable for flexible packaging and especially suitable for blending with EVOH. Information provided by EMS Grivory

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_EMS-Grivory-Grivory-CF-7-PA.php](http://www.lookpolymers.com/polymer_EMS-Grivory-Grivory-CF-7-PA.php)

Physical Properties	Metric	English	Comments
Density	1.08 g/cc	0.0390 lb/in <sup>3</sup>	ISO 1183
Water Absorption	7.0 %	7.0 %	ISO 62
Moisture Absorption	2.00 %	2.00 %	ISO 62
Melt Flow	100 g/10 min	100 g/10 min	(MVR) [cm <sup>3</sup> /10min]; ISO 1133

Thermal Properties	Metric	English	Comments
Melting Point	155 °C	311 °F	10°C/min; ISO 11357-1/-3

Optical Properties	Metric	English	Comments
Gloss	130 %	130 %	60°; ISO 2813

Descriptive Properties	Value	Comments
Food contact	EU Requirements	
Form	Granules	
Packaging	Oriented film	
Processing	Blown Film Extrusion	
	Film Extrusion	
	Other Extrusion	
Product Attributes	Barrier Properties	
	Co Polyamide	
	Flexible	
	High viscosity	

## Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)

Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China