

EPICHEM Epiryl PPO V0 Polyphenylene oxide

Category : Polymer , Thermoplastic , Polyphenylene Ether/PPO

Material Notes:

Characteristics: self-extinguishing V0 at 1,6 mm

Order this product through the following link:

http://www.lookpolymers.com/polymer_EPICHEM-Epiryl-PPO-V0-Polyphenylene-oxide.php

Physical Properties	Metric	English	Comments
Density	1.10 g/cc	0.0397 lb/in ³	ASTM D792, ISO 1183
Water Absorption	<= 0.10 % @Temperature 23.0 °C	<= 0.10 % @Temperature 73.4 °F	24h; ASTM D570, ISO 62
Linear Mold Shrinkage	0.0050 - 0.0070 cm/cm	0.0050 - 0.0070 in/in	ASTM D955
Melt Index of Compound	10 - 20 g/10 min @Load 1.20 kg, Temperature 300 °C	10 - 20 g/10 min @Load 2.65 lb, Temperature 572 °F	ASTM D1238, ISO 1133

Mechanical Properties	Metric	English	Comments
Hardness, Rockwell M	80	80	ASTM D785, ISO 2039/2
Tensile Strength, Yield	55.0 MPa	7980 psi	ASTM D638, ISO R527
Elongation at Break	50 %	50 %	ASTM D638, ISO R527
Flexural Strength	90.0 MPa	13100 psi	ASTM D790, ISO 178
Flexural Modulus	2.40 GPa	348 ksi	ASTM D790, ISO 178
Izod Impact, Notched	0.900 J/cm @Thickness 3.20 mm, Temperature -30.0 °C	1.69 ft-lb/in @Thickness 0.126 in, Temperature -22.0 °F	ASTM D256, ISO 180/4a
	1.80 J/cm @Thickness 3.20 mm, Temperature 0.000 °C	3.37 ft-lb/in @Thickness 0.126 in, Temperature 32.0 °F	ASTM D256, ISO 180/4a
	2.00 J/cm @Thickness 3.20 mm, Temperature 23.0 °C	3.75 ft-lb/in @Thickness 0.126 in, Temperature 73.4 °F	ASTM D256, ISO 180/4a

Thermal Properties	Metric	English	Comments
Hot Ball Pressure Test	>= 100 °C	>= 212 °F	BS 3456, IEC 335

Thermal Properties <small>Deflection Temperature at 1.8 MPa (104 psi)</small>	110 °C Metric	230 °F English	ASTM D648, ISO 75 Comments
Vicat Softening Point	120 °C @Load 5.00 kg	248 °F @Load 11.0 lb	120°C/min; ASTM D1525/B, ISO 306/B
	130 °C @Load 0.999 kg	266 °F @Load 2.20 lb	120°C/min; ASTM D1525/A, ISO 306/A
Flammability, UL94	V-0 @Thickness 1.60 mm	V-0 @Thickness 0.0630 in	
	V-0 @Thickness 3.20 mm	V-0 @Thickness 0.126 in	
Glow Wire Test	960 °C @Thickness 3.20 mm	1760 °F @Thickness 0.126 in	VDE 0471/P2-4, IEC 695
	960 °C @Thickness 2.00 mm	1760 °F @Thickness 0.0787 in	VDE 0471/P2-4, IEC 695

Electrical Properties	Metric	English	Comments
Surface Resistance	1.00e+14 ohm	1.00e+14 ohm	ASTM D257, IEC 93
Dielectric Constant	2.7 @Frequency 1000 Hz	2.7 @Frequency 1000 Hz	ASTM D150, IEC 250
Dielectric Strength	70.0 kV/mm	1780 kV/in	ASTM D149, IEC 243
Dissipation Factor	0.0070 @Frequency 1000 Hz	0.0070 @Frequency 1000 Hz	ASTM D150, IEC 250
Comparative Tracking Index	275 V	275 V	VDE 0303-P1, IEC 112

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China