Eastman 5282 LDPE 8% EVA Copolymer, High Clarity, High Impact Film Resin (discontinued **)

Category : Polymer , Film , Thermoplastic , Ethylene Vinyl Acetate , Ethylene Vinyl Acetate Copolymer (EVA), Film Grade

Material Notes:

Resin Type: CopolymerCharacteristics: Excellent Heat Seal Characteristics, Superior Impact Strength, Good Optical Properties, Low Slip, High Antiblock, Good Bubble Stability at High Draw Down SpeedsApplications: Ice Bags, Laminations, Liquid and Heavy Duty PackagingProcessing Conditions: Extruder 6.35 cm. Screw L/D Ratio 24:1. Die Opening 0.0762 cm. Blow-Up Ratio 2:1.Film properties below based on film thickness of 31.8 µm.Eastman Chemical Company sold its polyethylene business to Westlake Chemical Corporation in Dec. 2006. This grade no longer appears in the Westlake product line.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Eastman-5282-LDPE-8-EVA-Copolymer-High-Clarity-High-Impact-Film-Resin-nbspdiscontinued-.php

| Physical Properties | Metric | English | Comments |
|---------------------|--------------|---------------|--------------------------|
| Density | 0.932 g/cc | 0.0337 lb/in³ | ASTM D1505 |
| Melt Flow | 1.0 g/10 min | 1.0 g/10 min | Condition E; ASTM D 1238 |

| Mechanical Properties | Metric | English | Comments |
|-------------------------|---------------|-----------|---|
| Cocont Madulus MD | 0.110 GPa | 16.0 ksi | A C T NA D002 |
| Secant Modulus, MD | 0.110 6F a | 10.0 KSI | ASTM D882 |
| Secant Modulus, TD | 0.120 GPa | 17.4 ksi | ASTM D882 |
| Coefficient of Friction | 0.10 | 0.10 | ASTM D1894 |
| | | | |
| Dart Drop | 5.50 g/micron | 140 g/mil | F ₅₀ ; 1.5 in. dart/26 in. drop height; ASTM D 1709 |

| Optical Properties | Metric | English | Comments |
|-----------------------|--------|---------|---------------------------------|
| Haze | 6.5 % | 6.5 % | ASTM D2457 |
| Gloss | 63 % | 63 % | at 45°. ASTM D 2457 |
| | 100 % | 100 % | at 60°. ASTM D 2457 |
| Transmission, Visible | 90 % | 90 % | clear; thickness not quantified |

| Processing Properties | Metric | English | Comments |
|-----------------------|--------|---------|----------|
| Melt Temperature | 204 °C | 399 °F | |

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com



Email : sales@lookpolymers.com Tel : +86 021-51131842 Mobile : +86 13061808058 Skype : lookpolymers Address : United North Road 215,Fengxian District, Shanghai City,China