

## Eastman Aqua 20837 PET (discontinued \*\*)

Category : Polymer , Thermoplastic , Polyester, TP , Polyethylene Terephthalate (PET) , Polyethylene Terephthalate (PET), Unreinforced

### Material Notes:

Voridian Aqua thermoplastic polyesters are condensation polymers produced by a continuous melt-phase polymerization process followed by a solid-state polymerization process. Voridian Aqua polymer 20837 was developed for the European sparkling water market and is available in Europe only. Applications/Uses Water bottles

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_Eastman-Aqua-20837-PET-nbspdiscontinued-.php](http://www.lookpolymers.com/polymer_Eastman-Aqua-20837-PET-nbspdiscontinued-.php)

Physical Properties	Metric	English	Comments
Bulk Density	0.804 g/cc	0.0290 lb/in <sup>3</sup>	Poured; ASTM D1895
	0.881 g/cc	0.0318 lb/in <sup>3</sup>	Vibrated; ASTM D1895
Density	1.40 g/cc	0.0506 lb/in <sup>3</sup>	Crystalline Density; ASTM D1505
Melt Density	1.20 g/cc	0.0434 lb/in <sup>3</sup>	ASTM D1238
	@Temperature 285 °C	@Temperature 545 °F	
Particle Size	2500 µm	2500 µm	Pellet Size
Viscosity Measurement	0.74 - 0.78	0.74 - 0.78	Intrinsic; VGAS-A-AN-G-V-1

Thermal Properties	Metric	English	Comments
Heat of Fusion	61.0 J/g	26.2 BTU/lb	ASTM E793
Specific Heat Capacity	1.10 J/g-°C	0.263 BTU/lb-°F	ASTM E1269
	1.40 J/g-°C	0.335 BTU/lb-°F	ASTM E1269
	@Temperature 80.0 °C	@Temperature 176 °F	
	1.50 J/g-°C	0.359 BTU/lb-°F	ASTM E1269
	@Temperature 100 °C	@Temperature 212 °F	
1.90 J/g-°C	0.454 BTU/lb-°F	ASTM E1269	
@Temperature 200 °C	@Temperature 392 °F		
2.10 J/g-°C	0.502 BTU/lb-°F	ASTM E1269	
@Temperature 280 °C	@Temperature 536 °F		
Melting Point	248 °C	478 °F	Crystalline Peak Melting Point; ASTM D3418

Descriptive Properties	Value	Comments
------------------------	-------	----------

Acetaldehyde Descriptive Properties	<1 ppm Value	VKCA-A-AS-G-GC-0001 Comments
Color, CIE a*	-3.63 to -0.63	VGAS-A-AN-G-RS-001
Color, CIE b*	-1.33 to 2.12	VGAS-A-AN-G-RS-001
Color, CIE L*	81 min	VGAS-A-AN-G-RS-001
Fines, wt%, max	0.05	
Pellet Shape	Cubical	

## Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)

Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China