

Eastman DuraStar MN610 Polymer, Natural

Category : Polymer , Thermoplastic , Polyester, TP , Polycyclohexylenedimethylene Terephthalate (PCT) , Glycol-Modified PCT (PCTG) Copolyester

Material Notes:

Durastar MN610 polymer has excellent appearance and is nearly water-clear. Its most outstanding features are toughness, chemical resistance, and excellent processing characteristics. MN610 has very good toughness as shown by Izod impact resistance. Easy to process, it flows readily and fills intricate molds. Applications/Uses Medical

Order this product through the following link:

http://www.lookpolymers.com/polymer_Eastman-DuraStar-MN610-Polymer-Natural.php

Physical Properties	Metric	English	Comments
Specific Gravity	1.20 g/cc	1.20 g/cc	ASTM D792
Linear Mold Shrinkage	0.0020 - 0.0060 cm/cm @Thickness 3.20 mm	0.0020 - 0.0060 in/in @Thickness 0.126 in	ASTM D955

Mechanical Properties	Metric	English	Comments
Hardness, Rockwell R	103	103	ASTM D785
Tensile Strength at Break	46.0 MPa	6670 psi	ISO 527
	51.0 MPa	7400 psi	ASTM D638
Tensile Strength, Yield	47.0 MPa	6820 psi	ASTM D638
	47.0 MPa	6820 psi	ISO 527
Elongation at Break	200 %	200 %	ISO 527
	300 %	300 %	ASTM D638
Elongation at Yield	4.0 %	4.0 %	ISO 527
	5.0 %	5.0 %	ASTM D638
Tensile Modulus	1.80 GPa	261 ksi	ISO 527
Flexural Strength	65.0 MPa	9430 psi	ISO 178
Flexural Yield Strength	69.0 MPa	10000 psi	ASTM D790
Flexural Modulus	1.85 GPa	268 ksi	ISO 178
	2.00 GPa	290 ksi	ASTM D790
Izod Impact, Notched	0.400 J/cm @Temperature -40.0 °C	0.749 ft-lb/in @Temperature -40.0 °F	ASTM D256

Mechanical Properties	Metric <i>J/cm</i>	English <i>lb/in</i>	Comments
	@Temperature 23.0 °C	@Temperature 73.4 °F	ASTM D236
Izod Impact, Unnotched	NB	NB	ASTM D4812
	NB	NB	ASTM D4812
	@Temperature -40.0 °C	@Temperature -40.0 °F	
Izod Impact, Notched (ISO)	4.80 kJ/m ²	2.28 ft-lb/in ²	ISO 180
	@Temperature -40.0 °C	@Temperature -40.0 °F	
	7.80 kJ/m ²	3.71 ft-lb/in ²	ISO 180
	@Temperature 23.0 °C	@Temperature 73.4 °F	
Puncture Energy	42.0 J	31.0 ft-lb	Puncture Resistance @Max Load, 23°C; ASTM D3763
	48.0 J	35.4 ft-lb	Puncture Resistance at Max Load; ASTM D3763
	@Temperature -40.0 °C	@Temperature -40.0 °F	

Thermal Properties	Metric	English	Comments
Deflection Temperature at 0.46 MPa (66 psi)	74.0 °C	165 °F	ASTM D648
Deflection Temperature at 1.8 MPa (264 psi)	65.0 °C	149 °F	ASTM D648

Optical Properties	Metric	English	Comments
Haze	0.30 %	0.30 %	ASTM D1003
Transmission, Visible	89 %	89 %	Regular Transmittance; ASTM D1003
	91 %	91 %	Total Transmittance; ASTM D1003

Processing Properties	Metric	English	Comments
Melt Temperature	230 - 280 °C	446 - 536 °F	
Mold Temperature	15.0 - 30.0 °C	59.0 - 86.0 °F	
Drying Temperature	70.0 °C	158 °F	
Dry Time	3 hour	3 hour	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215, Fengxian District, Shanghai City, China