

Eastman E6838-997F Polyethylene (discontinued **)

Category : Polymer , Thermoplastic , Polyethylene (PE) , LDPE

Material Notes:

E6838-997F natural is a low density formulation with no slip or antiblock. Outstanding optical properties make this material an excellent choice for calendering and as a clarity filler in co-extruded applications. List of Applications: Food-contact applications E6838-997F meets the requirements of FDA regulations at 21 CFR 177.1520(c)(2.2) and may be used as a component of packages used for holding food during cooking. However, the polymer thickness in the form in which it contacts food shall not exceed 0.005 inches and contact is limited to non-alcoholic food because of a regulatory limitation for an adjuvant substance in this formulation. Information supplied by the manufacturer. Information from manufacturer data sheet. Eastman Chemical Company sold its polyethylene business to Westlake Chemical Corporation in Dec. 2006. This grade no longer appears in the Westlake product line.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Eastman-E6838-997F-Polyethylene-nbspdiscontinued-.php

Physical Properties	Metric	English	Comments
Density	0.921 g/cc	0.0333 lb/in ³	ASTM D4883
Moisture Vapor Transmission	18.6 cc-mm/m ² -24hr-atm	47.2 cc-mil/100 in ² -24hr-atm	ASTM F372
Oxygen Transmission	200 cc-mm/m ² -24hr-atm	508 cc-mil/100 in ² -24hr-atm	ASTM D1434
Thickness	32.0 microns	1.26 mil	
Melt Flow	2.0 g/10 min @Load 2.16 kg, Temperature 190 °C	2.0 g/10 min @Load 4.76 lb, Temperature 374 °F	ASTM D1238

Mechanical Properties	Metric	English	Comments
Film Tensile Strength at Yield, MD	24.0 MPa	3480 psi	ASTM D882
Film Tensile Strength at Yield, TD	10.0 MPa	1450 psi	ASTM D882
Film Elongation at Break, MD	350 %	350 %	ASTM D882
Film Elongation at Break, TD	550 %	550 %	ASTM D882
Secant Modulus, MD	0.172 GPa	24.9 ksi	1% Secant; ASTM D882
Secant Modulus, TD	0.193 GPa	28.0 ksi	1% Secant; ASTM D882
Coefficient of Friction	0.70	0.70	ASTM D1894
Elmendorf Tear Strength MD	350 g	350 g	
Elmendorf Tear Strength TD	180 g	180 g	

Mechanical Properties	Metric	English	Comments
Elmendorf Tear Strength, TD	5.60 g/micron	142 g/mil	ASTM D1922
Dart Drop	2.50 g/micron	63.5 g/mil	ASTM D1709A
Film Tensile Strength at Break, MD	24.0 MPa	3480 psi	ASTM D882
Film Tensile Strength at Break, TD	19.0 MPa	2760 psi	ASTM D882

Thermal Properties	Metric	English	Comments
Vicat Softening Point	95.0 °C	203 °F	ASTM D1525

Optical Properties	Metric	English	Comments
Haze	6.5 %	6.5 %	ASTM D1003
Gloss	60 %	60 %	at 45°; ASTM D2457
Transmission, Visible	25 %	25 %	ASTM D1746

Descriptive Properties	Value	Comments
Process	Film	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China