

## Eastman Ecdel PCCE 9965 Copolyester Ether Elastomer

Category : Polymer , Thermoplastic , Polyester, TP

### Material Notes:

ISO data as provided by the manufacturer, Eastman Chemical

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_Eastman-Ecdel-PCCE-9965-Copolyester-Ether-Elastomer.php](http://www.lookpolymers.com/polymer_Eastman-Ecdel-PCCE-9965-Copolyester-Ether-Elastomer.php)

Physical Properties	Metric	English	Comments
Density	1.13 g/cc	0.0408 lb/in <sup>3</sup>	

Mechanical Properties	Metric	English	Comments
Tensile Strength, Yield	12.0 MPa	1740 psi	50 mm/min
Elongation at Break	>= 50 %	>= 50 %	
Elongation at Yield	29 %	29 %	
Tensile Modulus	0.156 GPa	22.6 ksi	1mm/min
Charpy Impact Unnotched	NB	NB	
	NB	NB	
	@Temperature -30.0 °C	@Temperature -22.0 °F	
Charpy Impact, Notched	NB	NB	
	1.10 J/cm <sup>2</sup>	5.24 ft-lb/in <sup>2</sup>	
	@Temperature -30.0 °C	@Temperature -22.0 °F	

Thermal Properties	Metric	English	Comments
CTE, linear, Parallel to Flow	148 µm/m-°C	82.2 µin/in-°F	
	@Temperature 20.0 °C	@Temperature 68.0 °F	
CTE, linear, Transverse to Flow	139 µm/m-°C	77.2 µin/in-°F	
	@Temperature 20.0 °C	@Temperature 68.0 °F	
Melting Point	208 °C	406 °F	
Deflection Temperature at 0.46 MPa (66 psi)	57.0 °C	135 °F	
Deflection Temperature at 1.8 MPa (264 psi)	46.0 °C	115 °F	
Vicat Softening Point	56.0 °C	133 °F	

Class Transition Temp, Tg Thermal Properties	-3.00 °C Metric	26.6 °F English	Comments
Processing Properties	Metric	English	Comments
Melt Temperature	225 - 260 °C	437 - 500 °F	

## Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)

Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China