

Eastman P76CC PET (discontinued **)

Category : Polymer , Thermoplastic , Polyester, TP , Polyethylene Terephthalate (PET) , Polyethylene Terephthalate (PET), Unreinforced

Material Notes:

Voridian PET P76CC is used for dual ovenable containers and release paper. Applications/Uses Dual ovenable containers Release paper

Order this product through the following link:

http://www.lookpolymers.com/polymer_Eastman-P76CC-PET-nbspdiscontinued-.php

Physical Properties	Metric	English	Comments
Bulk Density	0.846 g/cc	0.0306 lb/in ³	Poured; ASTM D1895
	0.909 g/cc	0.0328 lb/in ³	Vibrated; ASTM D1895
Density	1.40 g/cc	0.0506 lb/in ³	Crystalline Density; ASTM D1505
Melt Density	1.20 g/cc	0.0434 lb/in ³	ASTM D1238
	@Temperature 285 °C	@Temperature 545 °F	
Viscosity Measurement	0.74 - 0.78	0.74 - 0.78	Intrinsic; EMN-A-AC-G-V-1

Thermal Properties	Metric	English	Comments
Melting Point	244 °C	471 °F	Crystalline Peak Melting Point; ASTM D3418

Descriptive Properties	Value	Comments
Acetaldehyde	<1ppm	VCSC-A-AN-G-GC-38
Color, CIE a*	-0.9 ± 1.5	VGAS-A-AN-G-RS-001
Color, CIE b*	-1.5 ± 1.0	VGAS-A-AN-G-RS-001
Color, CIE L*	78.5 min	VGAS-A-AN-G-RS-001
Fines, wt%, max	0.05	VGAS-A-AN-G-GA-1

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China