

## Eastman Provista ST Copolymer

Category : Polymer , Thermoplastic , Polyester, TP

### Material Notes:

Provista Copolymer ST is a resin specifically developed for profile extrusion where high clarity and gloss, toughness, and processability are critical. Provista Copolymer ST is a second-generation material that complements Provista by offering similar features, while providing greater toughness. Provista Copolymer ST is ideal in applications that place greater physical demands on the profile. Applications/Uses Packaging tubes Pricing channels Signage channels Plastic angle moldings Profiles Store fixtures Key Attributes Ease of processing Excellent chemical resistance Meets FDA regulations for food contact Sparkling clarity and high gloss Toughness with flexibility

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_Eastman-Provista-ST-Copolymer.php](http://www.lookpolymers.com/polymer_Eastman-Provista-ST-Copolymer.php)

Physical Properties	Metric	English	Comments
Specific Gravity	1.25 g/cc	1.25 g/cc	ASTM D792
Linear Mold Shrinkage	0.0030 cm/cm	0.0030 in/in	ASTM D955

Mechanical Properties	Metric	English	Comments
Hardness, Rockwell R	105	105	ASTM D785
Tensile Strength at Break	48.0 MPa	6960 psi	ASTM D638
Tensile Strength, Yield	47.0 MPa	6820 psi	ASTM D638
Elongation at Break	300 %	300 %	ASTM D638
Elongation at Yield	5.0 %	5.0 %	ASTM D638
Tensile Modulus	1.90 GPa	276 ksi	ASTM D638
Flexural Strength	65.0 MPa	9430 psi	ASTM D790
Flexural Modulus	1.90 GPa	276 ksi	ASTM D790
Izod Impact, Notched	0.630 J/cm	1.18 ft-lb/in	ASTM D256
	@Temperature -40.0 °C	@Temperature -40.0 °F	
	NB	NB	ASTM D256
	@Temperature 23.0 °C	@Temperature 73.4 °F	
Izod Impact, Unnotched	NB	NB	ASTM D4812
	NB	NB	ASTM D4812
	@Temperature -40.0 °C	@Temperature -40.0 °F	

Puncture Energy Mechanical Properties	41.0 J Metric	30.2 ft-lb English	Puncture Resistance @ Max Load, 23°C; ASTM D3763
	41.0 J	30.2 ft-lb	Puncture Resistance @Max Load, 23°C; ASTM D3763
	39.0 J @Temperature -40.0 °C	28.8 ft-lb @Temperature -40.0 °F	Puncture Resistance at Max Load; ASTM D3763

Thermal Properties	Metric	English	Comments
Deflection Temperature at 0.46 MPa (66 psi)	73.0 °C	163 °F	ASTM D648
Deflection Temperature at 1.8 MPa (264 psi)	63.0 °C	145 °F	ASTM D648
Vicat Softening Point	85.0 °C	185 °F	ASTM D1525

Optical Properties	Metric	English	Comments
Haze	1.3 %	1.3 %	ASTM D1003
Gloss	143 %	143 %	at 60°; ASTM D2457
Transmission, Visible	87 %	87 %	Regular Transmittance; ASTM D1003
	91 %	91 %	Total Transmittance; ASTM D1003

Descriptive Properties	Value	Comments
Color, CIE a*	-0.2	VGAS-A-AN-G-RS-001
Color, CIE b*	0.6	VGAS-A-AN-G-RS-001
Color, CIE L*	95	VGAS-A-AN-G-RS-001

## Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)

Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China