

## Elastocon TPE Technologies Elastocon® 8150B Thermoplastic Elastomer

Category : Polymer , Thermoplastic , Elastomer, TPE

### Material Notes:

Elastocon® 8150B is a black thermoplastic elastomer formulated for applications that require rubber-like properties and a good surface finish. Elastocon® 8150B is well suited for consumer goods and industrial applications requiring U.V. stability. Elastocon® 8150B can be overmolded to polypropylene. Information provided by Elastocon TPE Technologies, Inc.

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_Elastocon-TPE-Technologies-Elastocon-8150B-Thermoplastic-Elastomer.php](http://www.lookpolymers.com/polymer_Elastocon-TPE-Technologies-Elastocon-8150B-Thermoplastic-Elastomer.php)

Physical Properties	Metric	English	Comments
Specific Gravity	1.16 g/cc	1.16 g/cc	ASTM D792
Linear Mold Shrinkage, Flow	0.011 - 0.021 cm/cm	0.011 - 0.021 in/in	ASTM D955

Mechanical Properties	Metric	English	Comments
Hardness, Shore A	48	48	ASTM D2240
Tensile Strength	5.25 MPa	761 psi	ASTM D412
Elongation at Break	622 %	622 %	ASTM D412
100% Modulus	0.00253 GPa	0.367 ksi	ASTM D412
Compression Set	15 % @Temperature 20.0 °C, Time 79200 sec	15 % @Temperature 68.0 °F, Time 22.0 hour	ASTM D395B

Processing Properties	Metric	English	Comments
Feed Temperature	<= 79.4 °C	<= 175 °F	
Rear Barrel Temperature	174 - 191 °C	345 - 375 °F	
Front Barrel Temperature	179 - 196 °C	355 - 385 °F	
Nozzle Temperature	185 - 204 °C	365 - 400 °F	
Mold Temperature	21.1 - 37.8 °C	70.0 - 100 °F	
Back Pressure	0.345 - 0.689 MPa	50.0 - 100 psi	

Descriptive Properties	Value	Comments
Injection Rate	Moderate to Fast	

## **Contact Songhan Plastic Technology Co.,Ltd.**

**Website : [www.lookpolymers.com](http://www.lookpolymers.com)**

**Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)**

**Tel : +86 021-51131842**

**Mobile : +86 13061808058**

**Skype : lookpolymers**

**Address : United North Road 215,Fengxian District, Shanghai City,China**