

## Elektro-Isola Etronax MF G Phenolic, Cotton Fabric Reinforcement, Black, Tubes

Category : Polymer , Thermoset , Phenolic

**Material Notes:**

Description: Mechanical applications. Impact-resistant, noise-reducing, wear-resistant material. Well suited as a low-friction material. High wear resistance in aggressive and dust-filled environments. Can be lubricated with water, oil or grease. Good dry-run properties. Applications: Bearing bushings, rudder bearings and guide rings for hydraulic cylinders. Information provided by Elektro-Isola

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_Elektro-Isola-Etronax-MF-G-Phenolic-Cotton-Fabric-Reinforcement-Black-Tubes.php](http://www.lookpolymers.com/polymer_Elektro-Isola-Etronax-MF-G-Phenolic-Cotton-Fabric-Reinforcement-Black-Tubes.php)

Physical Properties	Metric	English	Comments
Density	1.30 g/cc @Thickness >=0.000 mm	0.0470 lb/in <sup>3</sup> @Thickness >=0.000 in	24hr/23°C/50% RH; ISO 1183-A; IEC/EN 61212-2 7.3
Water Absorption	0.25 %	0.25 %	24hr/50°C+24hr in water at 23°C; ISO 62-1; IEC/EN 61212-2 7.2

Mechanical Properties	Metric	English	Comments
Flexural Strength	100 MPa @Diameter >=100 mm	14500 psi @Diameter >=3.94 in	24hr/23°C/50% RH; ISO 178; IEC/EN 61212-2 5.1
Compressive Strength	180 MPa @Temperature 23.0 °C, Time 86400 sec	26100 psi @Temperature 73.4 °F, Time 24.0 hour	50% RH, Axial; ISO 604; IEC/EN 61212-2 5.2
Adhesive Bond Strength	140 MPa @Diameter <=100 mm	20300 psi @Diameter <=3.94 in	24hr/23°C/50% RH; IEC 60212-2; IEC/EN 61212-2 5.3

Thermal Properties	Metric	English	Comments
Maximum Service Temperature, Inert	100 °C @Thickness 3.00 mm, Time 7.20e+7 sec	212 °F @Thickness 0.118 in, Time 20000 hour	IEC 60695-11-10; IEC/EN 61212-2 7.1

### Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China