

## Elmer's Products Aron Alpha® 241F Cyanoacrylate Adhesive (Industrial Krazy Glue™)

Category : Polymer , Adhesive , Thermoset , Acrylic/Cyanoacrylate Adhesive

### Material Notes:

Surface insensitive adhesives, ultra-fast setting for porous, soft or tough-to-bond substrates. Series 200TX & Gel: No run, no stringing, excellent gap filling characteristics with good strength on a variety of materials. Low gap fill. Ethyl base monomer. Excellent on rubber/plastic substrates. Fair on metal substrates. Excellent on porous substrates. Military Spec MIL-A-46050C Type 2. Military Spec MIL-A-46050C Class 3. A primer is required for hard-to-bond materials such as polyethylene, polypropylene, acetal, PET, nylon, soft PVC, silicone rubber, and glass. General information about the Aron Alpha® product line: Cyanoacrylates are single component instant adhesives that bond a wide variety of surfaces with a strong, durable bond. They offer ease of application, a wide range of performance parameters, and reliable solvent-free bonding. Toagosei Co., Ltd. produces cyanoacrylates in Japan, marketed as Aron Alpha® in Japan, Cyanolit® in Europe, and Krazy Glue® in the US. Elmer's Products markets Krazy Glue® to the retail trade and Aron Alpha® to the industrial trade in North America. Information provided by Elmer's Products, Inc.

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_Elmers-Products-Aron-Alpha-241F-Cyanoacrylate-Adhesive-Industrial-Krazy-Glue.php](http://www.lookpolymers.com/polymer_Elmers-Products-Aron-Alpha-241F-Cyanoacrylate-Adhesive-Industrial-Krazy-Glue.php)

Physical Properties	Metric	English	Comments
Viscosity	40 cP	40 cP	

Mechanical Properties	Metric	English	Comments
Tensile Strength at Break	2.48 MPa	360 psi	vs. neoprene chloroprene (CR); 5 s set time
	19.3 MPa	2800 psi	vs. aluminum; 15 s set time
	31.7 MPa	4600 psi	vs. steel; 15 s set time
	34.5 MPa	5000 psi	vs. rigid PVC; 5 s set time
	34.5 MPa	5000 psi	vs. polycarbonate; 20 s set time

Thermal Properties	Metric	English	Comments
Maximum Service Temperature, Air	80.0 °C	176 °F	

Optical Properties	Metric	English	Comments
Transmission, Visible	80 %	80 %	Estimated; Manufacturer specifies clear but does not quantify.

Processing Properties	Metric	English	Comments
Processing Temperature	20.0 °C	68.0 °F	typically used at ambient temperature

Descriptive Properties	Value	Comments
Color	Clear	

**Contact Songhan Plastic Technology Co.,Ltd.**

Website : [www.lookpolymers.com](http://www.lookpolymers.com)  
Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)  
Tel : +86 021-51131842  
Mobile : +86 13061808058  
Skype : lookpolymers  
Address : United North Road 215,Fengxian District, Shanghai City,China