

Elmer's Products Aron Alpha® 403TB Cyanoacrylate Adhesive (Industrial Krazy Glue™)

Category : Polymer , Adhesive , Thermoset , Acrylic/Cyanoacrylate Adhesive

Material Notes:

Extra tough adhesives with highest heat, peeling, impact and thermal shock resistance. High gap fill. Ethyl base monomer. Excellent on rubber/plastic substrates. Excellent on metal substrates. Fair on porous substrates. Superior impact resistance. Good peel resistance. Very good thermal shock resistance. A primer is required for hard-to-bond materials such as polyethylene, polypropylene, acetal, PET, nylon, soft PVC, silicone rubber, and glass. General information about the Aron Alpha® product line: Cyanoacrylates are single component instant adhesives that bond a wide variety of surfaces with a strong, durable bond. They offer ease of application, a wide range of performance parameters, and reliable solvent-free bonding. Toagosei Co., Ltd. produces cyanoacrylates in Japan, marketed as Aron Alpha® in Japan, Cyanolit® in Europe, and Krazy Glue® in the US. Elmer's Products markets Krazy Glue® to the retail trade and Aron Alpha® to the industrial trade in North America. Information provided by Elmer's Products, Inc.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Elmers-Products-Aron-Alpha-403TB-Cyanoacrylate-Adhesive-Industrial-Krazy-Glue.php

Physical Properties	Metric	English	Comments
Viscosity	1000 cP	1000 cP	

Mechanical Properties	Metric	English	Comments
Tensile Strength at Break	2.48 MPa	360 psi	vs. neoprene chloroprene (CR); 30 s set time
	24.8 MPa	3600 psi	vs. rigid PVC; 15 s set time
	34.5 MPa	5000 psi	vs. polycarbonate; 15 s set time
	37.2 MPa	5400 psi	vs. aluminum; 90 s set time
	37.9 MPa	5500 psi	vs. steel; 60 s set time

Thermal Properties	Metric	English	Comments
Maximum Service Temperature, Air	120 °C	248 °F	

Processing Properties	Metric	English	Comments
Processing Temperature	20.0 °C	68.0 °F	typically used at ambient temperature

Descriptive Properties	Value	Comments
Color	Black	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China