

Ensinger Tecapeek® XP-113 Compression Molded PEEK Compound, 10% PTFE, 15% Graphite, and 3% Carbon Fiber

Category : Polymer , Thermoplastic , Polyketone , Polyetheretherketone (PEEK) , Polyetheretherketone, PEEK, Carbon Fiber Filled , Polyetheretherketone, PEEK, PTFE-Filled

Material Notes:

Ensinger Special Polymers offers over twenty different VICTREX® PEEK blends to choose from and has the capability to blend custom compounds for specific applications. Compression molding results in lower amounts of scrap, uniform physical properties and fewer molded-in stresses. TECAPEEK is a high-performance engineering thermoplastic. This semi-crystalline material has a balance of high temperature mechanical properties, chemical and steam resistance, superior wear properties and processability which makes it unique. Applications Include: Bearings and Bushings Down-hole instrumentation Wear Rings Ball Valve Seats Electrical Components Back-up and V-Rings Piston Rings and Rider Bands Information provided by Ensinger Special Polymers, Inc.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Ensinger-Tecapeek-XP-113-Compression-Molded-PEEK-Compound-10-PTFE-15-Graphite-and-3-Carbon-Fiber.php

Physical Properties	Metric	English	Comments
Density	1.47 g/cc	0.0531 lb/in ³	ASTM D792
Filler Content	25 %	25 %	

Mechanical Properties	Metric	English	Comments
Hardness, Rockwell M	96	96	ASTM D785
Tensile Strength	51.7 MPa	7500 psi	ASTM D638
Elongation at Break	1.3 %	1.3 %	ASTM D638
Tensile Modulus	4.83 GPa	700 ksi	ASTM D638
Flexural Strength	82.7 MPa	12000 psi	ASTM D790
Flexural Modulus	4.83 GPa	700 ksi	ASTM D790
Compressive Strength	117 MPa	17000 psi	ASTM D695

Thermal Properties	Metric	English	Comments
Melting Point	343 °C	649 °F	DSC

Descriptive Properties	Value	Comments
Color	Black	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China