

Ensinger Tecatron® XP-69 Compression Molded PPS Compound, 35% Fiberglass and Mineral Filled

Category: Polymer, Thermoplastic, Polyphenylene Sulfide (PPS), Polyphenylene Sulfide (PPS) with 40% Glass Fiber Filler

Material Notes:

Ensinger Special Polymers has over twenty different grades of TECATRON PPS available. Custom formulations can be blended to suit specific applications. Compression molding is amenable to short run production and yields products which are homogenous with low process stress. TECATRON PPS is a highly crystalline high-temperature thermoplastic with an excellent balance of cost, temperature resistance, strength, chemical resistance and flame retardance. TECATRON PPS is often used when long-term high-temperature performance and dimensional stability are a must, even in the presence of aggressive chemicals. Applications: Fuel Injectors Manifolds Pumps Pistons Gears V-Packing Gaskets Bearings Information provided by Ensinger Special Polymers, Inc.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Ensinger-Tecatron-XP-69-Compression-Molded-PPS-Compound-35-Fiberglass-and-Mineral-Filled.php

Physical Properties	Metric	English	Comments
Density	1.80 g/cc	0.0650 lb/in³	ASTM D792
Filler Content	35 %	35 %	

Mechanical Properties	Metric	English	Comments
Tensile Strength	32.4 MPa	4700 psi	ASTM D638
Elongation at Break	0.70 %	0.70 %	ASTM D638
Tensile Modulus	3.10 GPa	450 ksi	ASTM D638
Flexural Strength	49.6 MPa	7200 psi	ASTM D790
Flexural Modulus	8.27 GPa	1200 ksi	ASTM D790

Descriptive Properties	Value	Comments
Color	Dark Brown	

Contact Songhan Plastic Technology Co.,Ltd.

Website: www.lookpolymers.com Email: sales@lookpolymers.com

Tel: +86 021-51131842 Mobile: +86 13061808058 Skype: lookpolymers

Address: United North Road 215, Fengxian District, Shanghai City, China