

Entec Hypro™ PPC-CC30 Natural Copolymer Polypropylene, 30% Calcium Carbonate Filled

Category : Polymer , Thermoplastic , Polypropylene (PP) , Polypropylene with 30% Calcium Carbonate (CaCO₃) Filler

Material Notes:

Information provided by Entec

Order this product through the following link:

http://www.lookpolymers.com/polymer_Entec-Hypro-PPC-CC30-Natural-Copolymer-Polypropylene-30-Calcium-Carbonate-Filled.php

Physical Properties	Metric	English	Comments
Density	1.15 g/cc	0.0415 lb/in ³	ASTM D792
Melt Flow	10.0 g/10 min @Load 2.16 kg, Temperature 230 °C	10.0 g/10 min @Load 4.76 lb, Temperature 446 °F	ASTM D1238

Mechanical Properties	Metric	English	Comments
Tensile Strength, Yield	24.8 MPa	3600 psi	ASTM D638
Elongation at Break	80.0 %	80.0 %	ASTM D638
Elongation at Yield	5.00 %	5.00 %	ASTM D638
Flexural Strength	39.0 MPa	5660 psi	ASTM D790
Flexural Modulus	1.793 GPa	260.1 ksi	tangent; ASTM D790
Izod Impact, Notched	0.690 J/cm @Thickness 3.17 mm	1.29 ft-lb/in @Thickness 0.125 in	ASTM D256

Thermal Properties	Metric	English	Comments
Deflection Temperature at 0.46 MPa (66 psi)	104 °C	219 °F	ASTM D648

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China