

Eurofoam Porocell POR 304 CM-HD 200 EPDM Foam

Category : Polymer , Thermoset , Rubber or Thermoset Elastomer (TSE)

Material Notes:

Ethylene Propylene Diene Monomer Foam. Used for thermal insulation and soundproofing, antivibration and waterproofing; different types of gaskets. Information provided by Eurofoam s.r.l.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Eurofoam-Porocell-POR-304-CM-HD-200-EPDM-Foam.php

Physical Properties	Metric	English	Comments
Density	0.180 - 0.220 g/cc	0.00650 - 0.00795 lb/in ³	ISO 845-88
Water Absorption	<= 5.0 %	<= 5.0 %	ASTM D 1056

Mechanical Properties	Metric	English	Comments
Hardness, Shore OO	60 - 70	60 - 70	ASTM D 2240
Tensile Strength	0.600 MPa	87.0 psi	ASTM D 412
Elongation at Break	>= 150 %	>= 150 %	ASTM D 412
Compressive Yield Strength	0.0650 MPa	9.43 psi	ASTM 1056/85
	@Strain 25.0 %	@Strain 25.0 %	
Compressive Yield Strength	0.120 MPa	17.4 psi	ASTM 1056/85
	@Strain 50.0 %	@Strain 50.0 %	
Tear Strength	0.400 kN/m	2.28 pli	ASTM D 624

Thermal Properties	Metric	English	Comments
Maximum Service Temperature, Air	95.0 °C	203 °F	ASTM D 3575
Minimum Service Temperature, Air	-40.0 °C	-40.0 °F	ASTM D 3575
Flammability, UL94	HB	HB	HBF
Shrinkage	<= 5.0 %	<= 5.0 %	Linear; ASTM D 1204
	@Temperature 70.0 °C, Time 605000 sec	@Temperature 158 °F, Time 168 hour	

Descriptive Properties	Value	Comments
Cellular Structure	Closed	
Color	Black	

Descriptive Properties	Value	Comments
Declaration of Heavy Metal Absence	Conform	RoHS2002/95/EC
Fire Resistance	MV22 302	Pass
Vulcanization	Peroxide	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China