

## Eurofoam Porocell POR 304 CM-OPC EPDM Foam

Category : Polymer , Thermoset , Rubber or Thermoset Elastomer (TSE)

### Material Notes:

Ethylene Propylene Diene Monomer Foam. Used for thermal insulation and soundproofing, antivibration and waterproofing; different types of gaskets. Information provided by Eurofoam s.r.l.

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_Eurofoam-Porocell-POR-304-CM-OPC-EPDM-Foam.php](http://www.lookpolymers.com/polymer_Eurofoam-Porocell-POR-304-CM-OPC-EPDM-Foam.php)

Physical Properties	Metric	English	Comments
Density	0.600 - 0.800 g/cc	0.0217 - 0.0289 lb/in <sup>3</sup>	ISO 845-88

Mechanical Properties	Metric	English	Comments
Hardness, Shore OO	5.0 - 15	5.0 - 15	ASTM D 2240
Tensile Strength	0.100 MPa	14.5 psi	ASTM D 412
Elongation at Break	>= 150 %	>= 150 %	ASTM D 412
Compressive Yield Strength	0.00200 MPa @Strain 25.0 %	0.290 psi @Strain 25.0 %	ASTM 1056/85
Tear Strength	0.0700 kN/m	0.399 pli	ASTM D 624

Thermal Properties	Metric	English	Comments
Maximum Service Temperature, Air	95.0 °C	203 °F	ASTM D 3575
Minimum Service Temperature, Air	-40.0 °C	-40.0 °F	ASTM D 3575
Shrinkage	<= 5.0 % @Temperature 70.0 °C, Time 605000 sec	<= 5.0 % @Temperature 158 °F, Time 168 hour	Linear; ASTM D 1204

Descriptive Properties	Value	Comments
Cellular Structure	Open	
Color	Black	
Declaration of Heavy Metal Absence	Conform	RoHS2002/95/EC
Fire Resistance	MV22 302	Pass
Vulcanization	Peroxide	

## **Contact Songhan Plastic Technology Co.,Ltd.**

**Website : [www.lookpolymers.com](http://www.lookpolymers.com)**

**Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)**

**Tel : +86 021-51131842**

**Mobile : +86 13061808058**

**Skype : lookpolymers**

**Address : United North Road 215,Fengxian District, Shanghai City,China**