

Eurotec® Tecodur® PB70 GR25 NL100 XA20 PBT, 20% glass fiber reinforced, flame retardant - halogen (RoHS compliant), heat stabilized, natural

Category : Polymer , Thermoplastic , Polyester, TP , Polybutylene Terephthalate (PBT) , Polybutylene Terephthalate (PBT), 20% Glass Fiber Filled , Polybutylene Terephthalate (PBT), Heat Resistant

Material Notes:

Information provided by Eurotec®

Order this product through the following link:

http://www.lookpolymers.com/polymer_Eurotec-Tecodur-PB70-GR25-NL100-XA20-PBT-20-glass-fiber-reinforced-flame-retardant-halogen-RoHS-compliant-heat-stabilized-natural.php

Physical Properties	Metric	English	Comments
Density	1.61 g/cc	0.0582 lb/in ³	ISO 1183
Moisture Absorption	0.200 % @Temperature 23.0 °C	0.200 % @Temperature 73.4 °F	50% RH; ISO 960
Linear Mold Shrinkage, Flow	0.0030 cm/cm	0.0030 in/in	Eurotec
Linear Mold Shrinkage, Transverse	0.010 cm/cm	0.010 in/in	Eurotec

Mechanical Properties	Metric	English	Comments
Tensile Strength at Break	125 MPa	18100 psi	ISO 527
Elongation at Break	2.5 %	2.5 %	ISO 527
Tensile Modulus	9.50 GPa	1380 ksi	ISO 527
Izod Impact, Notched (ISO)	8.00 kJ/m ² @Temperature -30.0 °C	3.81 ft-lb/in ² @Temperature -22.0 °F	ISO 180/1A
	9.00 kJ/m ² @Temperature 23.0 °C	4.28 ft-lb/in ² @Temperature 73.4 °F	ISO 180/1A
Izod Impact, Unnotched (ISO)	55.0 kJ/m ² @Temperature -30.0 °C	26.2 ft-lb/in ² @Temperature -22.0 °F	ISO 180/1U
	60.0 kJ/m ² @Temperature 23.0 °C	28.6 ft-lb/in ² @Temperature 73.4 °F	ISO 180/1U

Thermal Properties	Metric	English	Comments
Melting Point	225 °C	437 °F	[10 K/min], ISO 11357
Deflection Temperature at 0.46 MPa (66 psi)	215 °C	419 °F	ISO 75

Thermal Properties <small>Deflection Temperature at 1.8 MPa (104 psi)</small>	Metric	English	Comments
Flammability, UL94	V-2	V-2	
	@Thickness 0.750 mm	@Thickness 0.0295 in	
	V-0	V-0	
	@Thickness 1.60 mm	@Thickness 0.0630 in	
Glow Wire Test	960 °C	1760 °F	GWFI; IEC 60695
	@Thickness 2.00 mm	@Thickness 0.0787 in	

Electrical Properties	Metric	English	Comments
Volume Resistivity	1.00e+16 ohm-cm	1.00e+16 ohm-cm	IEC 60093
Surface Resistance	1.00e+14 ohm	1.00e+14 ohm	IEC 60093
Comparative Tracking Index	225 V	225 V	Solution A; IEC 60112

Processing Properties	Metric	English	Comments
Processing Temperature	230 - 260 °C	446 - 500 °F	
Feed Temperature	50.0 - 70.0 °C	122 - 158 °F	Throat
Mold Temperature	50.0 - 100 °C	122 - 212 °F	
Drying Temperature	120 °C	248 °F	
Dry Time	2.00 - 4.00 hour	2.00 - 4.00 hour	
Moisture Content	<= 0.080 %	<= 0.080 %	ISO 960
Hold Pressure	40.0 - 80.0 MPa	5800 - 11600 psi	

Descriptive Properties	Value	Comments
Back Pressure	Low	
Injection Speed	Medium - Fast	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215, Fengxian District, Shanghai City, China