

Eurotec® Tecodur® PB70 GR35 NL100 HS01 PBT/PET, 35% glass fiber reinforced, heat stabilized, natural

Category : Polymer , Thermoplastic , Polyester, TP , Polybutylene Terephthalate (PBT) , PBT + PET Blend, Glass Filled , Polybutylene Terephthalate (PBT), Heat Resistant , Polyethylene Terephthalate (PET)

Material Notes:

Information provided by Eurotec®

Order this product through the following link:

http://www.lookpolymers.com/polymer_Eurotec-Tecodur-PB70-GR35-NL100-HS01-PBTPET-35-glass-fiber-reinforced-heat-stabilized-natural.php

Physical Properties	Metric	English	Comments
Density	1.58 g/cc	0.0571 lb/in ³	ISO 1183
Moisture Absorption	0.100 % @Temperature 23.0 °C	0.100 % @Temperature 73.4 °F	50% RH; ISO 960

Mechanical Properties	Metric	English	Comments
Tensile Strength at Break	140 MPa	20300 psi	ISO 527
Elongation at Break	1.5 %	1.5 %	ISO 527
Tensile Modulus	12.0 GPa	1740 ksi	ISO 527
Izod Impact, Notched (ISO)	8.00 kJ/m ² @Temperature -30.0 °C	3.81 ft-lb/in ² @Temperature -22.0 °F	ISO 180/1A
	9.00 kJ/m ² @Temperature 23.0 °C	4.28 ft-lb/in ² @Temperature 73.4 °F	ISO 180/1A

Thermal Properties	Metric	English	Comments
Melting Point	225 °C	437 °F	[10 K/min], ISO 11357
Deflection Temperature at 0.46 MPa (66 psi)	215 °C	419 °F	ISO 75
Deflection Temperature at 1.8 MPa (264 psi)	195 °C	383 °F	ISO 75
Flammability, UL94	HB @Thickness 1.60 mm	HB @Thickness 0.0630 in	
	HB @Thickness 0.750 mm	HB @Thickness 0.0295 in	

Electrical Properties	Metric	English	Comments
Volume Resistivity	1.00e+16 ohm-cm	1.00e+16 ohm-cm	IEC 60093
Surface Resistance	1.00e+14 ohm	1.00e+14 ohm	IEC 60093

Processing Properties	Metric	English	Comments
Processing Temperature	260 - 280 °C	500 - 536 °F	
Feed Temperature	50.0 - 70.0 °C	122 - 158 °F	Throat
Mold Temperature	60.0 - 110 °C	140 - 230 °F	
Drying Temperature	120 °C	248 °F	
Dry Time	4.00 - 6.00 hour	4.00 - 6.00 hour	
Moisture Content	<= 0.080 %	<= 0.080 %	ISO 960
Hold Pressure	40.0 - 80.0 MPa	5800 - 11600 psi	

Descriptive Properties	Value	Comments
Back Pressure	Low	
Injection Speed	Fast	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China